

InElec® PCSS15HF

Americhem - Polycarbonate

General Information

Product Description

15% STAINLESS STEEL FIBER REINFORCED, ELECTRICALLY CONDUCTIVE, EMI/RFI SHIELDING, HIGH FLOW POLYCARBONATE

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Stainless Steel Fiber, 15% Filler by Weight		
Features	• Electrically Conductive • Electromagnetic Shielding (EMI)	• ESD Protection • High Flow	• Permanent Antistatic • Radio Frequency Shielding (RFI)
Uses	• Automotive Applications • Closures • Connectors • Consumer Applications	• Electrical/Electronic Applications • Engineering Parts • Household Goods • Housings	• Industrial Applications • Industrial Parts • Office Automation Equipment
Forms	• Pellets		
Processing Method	• Injection Molding		

 Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.37		ASTM D792
Molding Shrinkage - Flow (0.125 in)	4.0E-3 to 6.0E-3	in/in	ASTM D955
Mechanical			
Tensile Modulus	420000	psi	ASTM D638
Tensile Strength	9000	psi	ASTM D638
Tensile Elongation (Yield)	4.0 to 6.0	%	ASTM D638
Flexural Modulus	420000	psi	ASTM D790
Flexural Strength (Yield)	15000	psi	ASTM D790
Impact			
Notched Izod Impact	1.2	ft·lb/in	ASTM D256
Thermal			
Deflection Temperature Under Load (264 psi, Unannealed)	255	°F	ASTM D648
Electrical			
Surface Resistivity	< 1.0E+4	ohms	ASTM D257

Processing Information

	Nominal Value	Unit
Injection		
Drying Temperature	250	°F
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.020	%
Processing (Melt) Temp	580 to 620	°F
Mold Temperature	180 to 240	°F
Back Pressure	50.0 to 100	psi
Screw Speed	40 to 70	rpm

