

Makrolon® 1260

Covestro - Polycarbonates - *Polycarbonate*

General Information

Product Description

MVR (300°C/1.2 kg) 34 cm³/10 min; impact modified; low viscosity; easy release; injection molding - melt temperature 280 - 320°C

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• Impact Modifier		
Features	• Good Mold Release	• Impact Modified	• Low Viscosity
RoHS Compliance	• RoHS Compliant		
Processing Method	• Injection Molding		
ISO Designation	• ISO 7391-PC,MPR,(,)-24-9		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.20	g/cm ³	ISO 1183
Apparent (Bulk) Density ²	0.64	g/cm ³	ISO 60
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	36	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	33	cm ³ /10min	ISO 1133
Molding Shrinkage			
Across Flow	0.50 to 0.70	%	ISO 2577
Flow	0.50 to 0.70	%	ISO 2577
Across Flow : 536°F, 0.0787 in ³	0.70	%	ISO 294-4
Flow : 0.0787 in ³	0.65	%	ISO 294-4
Water Absorption (Saturation, 73°F)	0.30	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.12	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	341000	psi	ISO 527-1/1
Tensile Stress (Yield, 73°F)	9140	psi	ISO 527-2/50
Tensile Stress (Break, 73°F)	7980	psi	ISO 527-2/50
Tensile Strain (Yield, 73°F)	5.8	%	ISO 527-2/50
Tensile Strain (Break, 73°F)	100	%	ISO 527-2/50
Nominal Tensile Strain at Break (73°F)	> 50	%	ISO 527-2/50
Flexural Modulus ⁴ (73°F)	341000	psi	ISO 178
Flexural Stress ⁴			ISO 178
73°F	13500	psi	
3.5% Strain, 73°F	10400	psi	
Flexural Strain at Flexural Strength ⁵ (73°F)	6.8	%	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁶			ISO 179/1eA
-22°F, Complete Break	6.7	ft·lb/in ²	
73°F, Partial Break	26	ft·lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-76°F	No Break		
-22°F	No Break		
73°F	No Break		
Notched Izod Impact Strength ⁶			ISO 180/A



-22°F, Complete Break	7.1	ft·lb/in ²	
73°F, Partial Break	24	ft·lb/in ²	
Multi-Axial Instrumented Impact Energy			ISO 6603-2
-22°F	40.6	ft·lb	
73°F	36.9	ft·lb	
Multi-Axial Instrumented Impact Peak Force			ISO 6603-2
-22°F	1280	lbf	
73°F	1080	lbf	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	16500	psi	ISO 2039-1
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	275	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	252	°F	ISO 75-2/A
Glass Transition Temperature ⁷	288	°F	ISO 11357-2
Vicat Softening Temperature			
--	289	°F	ISO 306/B120
--	288	°F	ISO 306/B50
Ball Pressure Test (273°F)	Pass		IEC 60695-10-2
CLTE - Flow (73 to 131°F)	3.9E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F)	3.9E-5	in/in/°F	ISO 11359-2
Thermal Conductivity ⁸ (73°F)	1.4	Btu·in/hr/ft ² /°F	ISO 8302
RTI Elec (0.06 in)	257	°F	UL 746B
RTI Imp (0.06 in)	221	°F	UL 746B
RTI Str (0.06 in)	239	°F	UL 746B
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity (73°F)	1.0E+16	ohms·cm	IEC 60093
Electric Strength (73°F, 0.0394 in)	860	V/mil	IEC 60243-1
Relative Permittivity			IEC 60250
73°F, 100 Hz	3.10		
73°F, 1 MHz	3.00		
Dissipation Factor			IEC 60250
73°F, 100 Hz	1.0E-3		
73°F, 1 MHz	0.010		
Comparative Tracking Index			IEC 60112
Solution A	250	V	
Solution B	125	V	
Electrolytic Corrosion (73°F)	A1		IEC 60426
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.030 in)	V-2		UL 94
Glow Wire Flammability Index			IEC 60695-2-12
0.030 in	1610	°F	
0.06 in	1650	°F	
0.12 in	1760	°F	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.030 in	1610	°F	
0.06 in	1610	°F	
0.12 in	1650	°F	
Oxygen Index ⁹	30	%	ISO 4589-2
Burning Rate ¹⁰ (> 39.4 mil)	passed		ISO 3795
Flash Ignition Temperature	860	°F	ASTM D1929
Needle Flame Test			IEC 60695-11-5
59.1 mil ¹¹	5	sec	
59.1 mil ¹²	60	sec	
78.7 mil ¹¹	5	sec	
78.7 mil ¹²	120	sec	
Temperature	1004	°F	ASTM

Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Dry Air Dryer	248	°F
Drying Time - Dry Air Dryer	2.0 to 3.0	hr
Suggested Max Moisture	< 0.020	%
Suggested Shot Size	30 to 70	%
Rear Temperature	482 to 500	°F
Middle Temperature	518 to 536	°F
Front Temperature	536 to 554	°F
Nozzle Temperature	554 to 572	°F
Processing (Melt) Temp	536 to 608	°F
Mold Temperature	176 to 248	°F
Back Pressure	725 to 2180	psi
Vent Depth	9.8E-4 to 3.0E-3	in

Injection Notes

Peripheral Screw Speed: 0.05 - 0.2 m/s
Standard Melt Temperature: 300°C
Hold Pressure (% of Injection Pressure): 50 - 75%

Notes

- ¹ Typical properties: these are not to be construed as specifications.
- ² Pellets
- ³ 60x60x2mm, 500 bar
- ⁴ 0.079 in/min
- ⁵ 2.0 mm/min
- ⁶ 3 mm
- ⁷ 10°C/min
- ⁸ Across Flow
- ⁹ Procedure A
- ¹⁰ US-FMVSS
- ¹¹ Method K
- ¹² Method F

