

LATIOHM 87/24-09UV PD01 G/10

 LATI INDUSTRIA TERMOPLASTICI SPA - *Polycarbonate*
General Information
Product Description

Semiconductive/dissipative product based on Polycarbonate (PC). UV stabilised. Glass fibres. PFAS-free product.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Glass Fiber		
Additive	• UV Stabilizer		
Features	• Antistatic	• High Heat Resistance	• UV Stabilized
	• Electrically Conductive	• PFAS Free	
Uses	• High Temperature Applications		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.35	g/cm ³	ISO 1183
Molding Shrinkage ²			ISO 294-4
Across Flow : 0.0787 in	0.40 to 0.60	%	
Flow : 0.0787 in	0.15 to 0.35	%	
Water Absorption ³ (Saturation, 73°F)	0.10	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	1.35E+6	psi	ISO 527-1/1
Tensile Stress (Break, 73°F)	18900	psi	ISO 527-2/5
Tensile Strain (Break, 73°F)	2.1	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.9	ft·lb/in ²	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	19	ft·lb/in ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	293	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	284	°F	ISO 75-2/A
Vicat Softening Temperature	302	°F	ISO 306/B120
CLTE - Flow (86 to 212°F)	1.4E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (86 to 212°F)	3.1E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	3.0E+3	ohms	ASTM D257
Volume Resistivity	4.0E+4	ohms·cm	ASTM D257
Electromagnetic Reflection - Bekiscan - CP	88	%	

Notes
¹ Typical properties: these are not to be construed as specifications.

² 60 MPa

³ in air
