

Makrolon® 6265 X

Covestro - Polycarbonates - *Polycarbonate*

General Information

Product Description

MVR (300°C/1.2 kg) 19 cm³/10 min; flame retardant; UL 94V-0/1.5 mm; low viscosity; easy release; injection molding - melt temperature 280 - 320°C; available in opaque colors only

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• Flame Retardant		
Features	• Flame Retardant	• Good Mold Release	• Low Viscosity
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Opaque	
Processing Method	• Injection Molding		
ISO Designation	• ISO 7391-PC,MFR,(..)-18-9		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.20	g/cm³	ISO 1183
Apparent (Bulk) Density ²	0.64	g/cm³	ISO 60
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	20	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	19	cm³/10min	ISO 1133
Molding Shrinkage			
Across Flow	0.50 to 0.70	%	ISO 2577
Flow	0.50 to 0.70	%	ISO 2577
Across Flow : 536°F, 0.0787 in ³	0.65	%	ISO 294-4
Flow : 0.0787 in ³	0.65	%	ISO 294-4
Water Absorption (Saturation, 73°F)	0.30	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.12	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	348000	psi	ISO 527-1/1
Tensile Stress (Yield, 73°F)	9430	psi	ISO 527-2/50
Tensile Stress (Break, 73°F)	9430	psi	ISO 527-2/50
Tensile Strain (Yield, 73°F)	6.0	%	ISO 527-2/50
Tensile Strain (Break, 73°F)	120	%	ISO 527-2/50
Nominal Tensile Strain at Break (73°F)	> 50	%	ISO 527-2/50
Tensile Creep Modulus (1 hr)	319000	psi	ISO 899-1
Tensile Creep Modulus (1000 hr)	276000	psi	ISO 899-1
Flexural Modulus ⁴ (73°F)	348000	psi	ISO 178
Flexural Stress ⁴			ISO 178
73°F	13900	psi	
3.5% Strain, 73°F	10600	psi	
Flexural Strain at Flexural Strength ⁵ (73°F)	7.0	%	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁶			ISO 179/1eA
-22°F, Complete Break	5.7	ft·lb/in²	
73°F, Partial Break	31	ft·lb/in²	
Charpy Unnotched Impact Strength			ISO 179/1eU



-76°F	No Break	
-22°F	No Break	
73°F	No Break	
Notched Izod Impact Strength ⁶		ISO 180/A
-22°F, Complete Break	5.2 ft·lb/in ²	
73°F, Partial Break	7.1 ft·lb/in ²	
Multi-Axial Instrumented Impact Energy		ISO 6603-2
-22°F	40.6 ft·lb	
73°F	36.9 ft·lb	
Multi-Axial Instrumented Impact Peak Force		ISO 6603-2
-22°F	1330 lbf	
73°F	1120 lbf	
Hardness	Nominal Value Unit	Test Method
Ball Indentation Hardness	16700 psi	ISO 2039-1
Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	279 °F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	255 °F	ISO 75-2/A
Glass Transition Temperature ⁷	291 °F	ISO 11357-2
Vicat Softening Temperature		
--	295 °F	ISO 306/B120
--	293 °F	ISO 306/B50
Ball Pressure Test (277°F)	Pass	IEC 60695-10-2
CLTE - Flow (73 to 131°F)	3.6E-5 in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F)	3.6E-5 in/in/°F	ISO 11359-2
Thermal Conductivity ⁸ (73°F)	1.4 Btu·in/hr/ft ² /°F	ISO 8302
RTI Elec (0.06 in)	257 °F	UL 746B
RTI Imp (0.06 in)	239 °F	UL 746B
RTI Str (0.06 in)	257 °F	UL 746B
Electrical	Nominal Value Unit	Test Method
Surface Resistivity	1.0E+16 ohms	IEC 60093
Volume Resistivity (73°F)	1.0E+16 ohms·cm	IEC 60093
Electric Strength (73°F, 0.0394 in)	860 V/mil	IEC 60243-1
Relative Permittivity		IEC 60250
73°F, 100 Hz	3.10	
73°F, 1 MHz	3.00	
Dissipation Factor		IEC 60250
73°F, 100 Hz	8.0E-4	
73°F, 1 MHz	9.0E-3	
Comparative Tracking Index		IEC 60112
Solution A	225 V	
Solution B	125 V	
Electrolytic Corrosion (73°F)	A1	IEC 60426
Flammability	Nominal Value Unit	Test Method
Flame Rating (0.06 in)	V-0	UL 94
Glow Wire Flammability Index		IEC 60695-2-12
0.030 in	1760 °F	
0.06 in	1760 °F	
0.12 in	1760 °F	
Glow Wire Ignition Temperature		IEC 60695-2-13
0.030 in	1610 °F	
0.06 in	1650 °F	
0.12 in	1650 °F	
Oxygen Index ⁹	36 %	ISO 4589-2
Application of Flame from Small Burner ¹⁰ (78.7 mil)	K1, F1	DIN 53438-1, -3
Burning Rate ¹¹ (> 39.4 mil)	passed	ISO 3795
Flash Ignition Temperature	860 °F	ASTM D1929
Flash Test		IEC 60695-2-10
	120 sec	
	120 sec	
	120 sec	

78.7 mil ¹³	120 sec	
0.12 in ¹²	120 sec	
0.12 in ¹³	120 sec	
Self Ignition Temperature	986 °F	ASTM D1929

Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Dry Air Dryer	248	°F
Drying Time - Dry Air Dryer	2.0 to 3.0	hr
Suggested Max Moisture	< 0.020	%
Suggested Shot Size	30 to 70	%
Rear Temperature	482 to 500	°F
Middle Temperature	518 to 536	°F
Front Temperature	536 to 554	°F
Nozzle Temperature	554 to 572	°F
Processing (Melt) Temp	536 to 608	°F
Mold Temperature	176 to 248	°F
Back Pressure	725 to 2180	psi
Vent Depth	9.8E-4 to 3.0E-3	in

Injection Notes

Peripheral Screw Speed: 0.05 - 0.2 m/s
Standard Melt Temperature: 300°C
Hold Pressure (% of Injection Pressure): 50 - 75%

Notes

¹ Typical properties: these are not to be construed as specifications.

² Pellets

³ 60x60x2mm, 500 bar

⁴ 0.079 in/min

⁵ 2.0 mm/min

⁶ 3 mm

⁷ 10°C/min

⁸ Across Flow

⁹ Procedure A

¹⁰ Method K and F

¹¹ US-FMVSS

¹² Method K

¹³ Method F

