

Makrolon® 2807 RE

Covestro - Polycarbonates - *Polycarbonate*

General Information

Product Description

MVR (300°C/1.2 kg) 9.0 cm³/10 min; general purpose; medium viscosity; UV stabilized; easy release; injection molding - melt temperature 280 - 320°C; available in transparent, translucent and opaque colors

Partially bio-circular grade / Attributed via mass balance (according to ISCC PLUS Standard).

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Asia Pacific • Europe • Latin America • North America
Additive	• UV Stabilizer
Features	• General Purpose • Good Mold Release • Medium Viscosity • UV Stabilized
Uses	• General Purpose
Agency Ratings	• ISCC PLUS
RoHS Compliance	• RoHS Compliant
Appearance	• Clear/Transparent • Colors Available • Opaque • Translucent
Processing Method	• Injection Molding
ISO Designation	• PC

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.20	g/cm ³	ISO 1183
Apparent (Bulk) Density ²	0.66	g/cm ³	ISO 60
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	9.0	cm ³ /10min	ISO 1133
Molding Shrinkage			
Across Flow	0.60 to 0.80	%	ISO 2577
Flow	0.60 to 0.80	%	ISO 2577
Across Flow : 536°F, 0.0787 in ³	0.70	%	ISO 294-4
Flow : 0.0787 in ³	0.65	%	ISO 294-4
Water Absorption (Saturation, 73°F)	0.30	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.12	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	348000	psi	ISO 527-1/1
Tensile Stress (Yield, 73°F)	9570	psi	ISO 527-2/50
Tensile Stress (Break, 73°F)	10200	psi	ISO 527-2/50
Tensile Strain (Yield, 73°F)	6.1	%	ISO 527-2/50
Tensile Strain (Break, 73°F)	130	%	ISO 527-2/50
Nominal Tensile Strain at Break (73°F)	> 50	%	ISO 527-2/50
Tensile Creep Modulus (1 hr)	319000	psi	ISO 899-1
Tensile Creep Modulus (1000 hr)	276000	psi	ISO 899-1
Flexural Modulus ⁴ (73°F)	348000	psi	ISO 178
Flexural Stress ⁴			ISO 178
73°F	14200	psi	
3.5% Strain, 73°F	10700	psi	
Flexural Strain at Flexural Strength ⁵ (73°F)	7.0	%	ISO 178



Films	Nominal Value	Unit	Test Method
Water Vapor Transmission Rate (73°F, 85% RH, 3.9 mil)	0.97	g/100 in ² /24 hr	ISO 15106-1
Carbon Dioxide Permeability (73°F, 1.0 mil)	16900	cm ³ /m ² /bar/24 hr	ISO 2556
Gas Permeation			ISO 2556
Carbon Dioxide : 3.9 mil	3800	cm ³ /m ² /bar/24 hr	
Nitrogen : 1.0 mil	510	cm ³ /m ² /bar/24 hr	
Nitrogen : 3.9 mil	120	cm ³ /m ² /bar/24 hr	
Oxygen : 1.0 mil	2760	cm ³ /m ² /bar/24 hr	
Oxygen : 3.9 mil	650	cm ³ /m ² /bar/24 hr	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁶			ISO 179/1eA
-22°F, Complete Break	6.7	ft·lb/in ²	
73°F, Partial Break	36	ft·lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-76°F	No Break		
-22°F	No Break		
73°F	No Break		
Notched Izod Impact Strength ⁶			ISO 180/A
-22°F, Complete Break	7.1	ft·lb/in ²	
73°F, Partial Break	33	ft·lb/in ²	
Multi-Axial Instrumented Impact Energy			ISO 6603-2
-22°F	47.9	ft·lb	
73°F	44.3	ft·lb	
Multi-Axial Instrumented Impact Peak Force			ISO 6603-2
-22°F	1420	lbf	
73°F	1210	lbf	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	16700	psi	ISO 2039-1
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	277	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	255	°F	ISO 75-2/A
Glass Transition Temperature ⁷	291	°F	ISO 11357-2
Vicat Softening Temperature			
--	293	°F	ISO 306/B120
--	289	°F	ISO 306/B50
Ball Pressure Test (275°F)	Pass		IEC 60695-10-2
CLTE - Flow (73 to 131°F)	3.6E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F)	3.6E-5	in/in/°F	ISO 11359-2
Thermal Conductivity ⁸ (73°F)	1.4	Btu·in/hr/ft ² /°F	ISO 8302
RTI Elec (0.06 in)	257	°F	UL 746B
RTI Imp (0.06 in)	239	°F	UL 746B
RTI Str (0.06 in)	257	°F	UL 746B
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity (73°F)	1.0E+16	ohms·cm	IEC 60093
Electric Strength (73°F, 0.0394 in)	860	V/mil	IEC 60243-1
Relative Permittivity			IEC 60250
73°F, 100 Hz	3.10		
73°F, 1 MHz	3.00		
Dissipation Factor			IEC 60250
73°F, 100 Hz	5.0E-4		
73°F, 1 MHz	9.0E-3		
Comparative Tracking Index			IEC 60112
Solution A	250	V	
Solution B	125	V	
Electrolytic Corrosion (73°F)	A1		IEC 60426
	Nominal Value	Unit	Test Method
	HB		UL 94
	V-2		

Glow Wire Flammability Index		IEC 60695-2-12
0.030 in	1560 °F	
0.06 in	1560 °F	
0.12 in	1710 °F	
Glow Wire Ignition Temperature		IEC 60695-2-13
0.030 in	1610 °F	
0.06 in	1610 °F	
0.12 in	1610 °F	
Oxygen Index ⁹	28 %	ISO 4589-2
Application of Flame from Small Burner ¹⁰ (78.7 mil)	K1, F1	DIN 53438-1, -3
Burning Rate ¹¹ (> 39.4 mil)	passed	ISO 3795
Flash Ignition Temperature	896 °F	ASTM D1929
Glow Wire Test		EDF HN60 E.02
59.1 mil	1382 °F	
0.12 in	1382 °F	
Needle Flame Test		IEC 60695-11-5
59.1 mil ¹²	60 sec	
59.1 mil ¹³	5 sec	
78.7 mil ¹²	60 sec	
78.7 mil ¹³	5 sec	
0.12 in ¹³	10 sec	
0.12 in ¹²	120 sec	
Self Ignition Temperature	1022 °F	ASTM D1929
Optical	Nominal Value Unit	Test Method
Refractive Index ¹⁴	1.586	ISO 489
Light Transmittance		ISO 13468-2
39.37 mil	89.0 %	
78.74 mil	89.0 %	
118.1 mil	88.0 %	
157.5 mil	87.0 %	
Haze (118.1 mil)	< 0.800 %	ISO 14782

Processing Information

	Nominal Value	Unit
Injection		
Drying Temperature - Dry Air Dryer	248	°F
Drying Time - Dry Air Dryer	2.0 to 3.0	hr
Suggested Max Moisture	< 0.020	%
Suggested Shot Size	30 to 70	%
Rear Temperature	482 to 500	°F
Middle Temperature	518 to 536	°F
Front Temperature	536 to 554	°F
Nozzle Temperature	554 to 572	°F
Processing (Melt) Temp	536 to 608	°F
Mold Temperature	176 to 248	°F
Back Pressure	725 to 2180	psi
Vent Depth	9.8E-4 to 3.0E-3	in

Injection Notes

Peripheral Screw Speed: 0.05 - 0.2 m/s
Hold Pressure (% of Injection Pressure): 50 - 75%
Standard Melt Temperature: 300°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² Pellets

³ 60x60x2mm, 500 bar

⁴ 0.079 in/min



⁹ Procedure A

¹⁰ Method K and F

¹¹ US-FMVSS

¹² Method F

¹³ Method K

¹⁴ Method A

