

Makrolon® 3106

Covestro - Polycarbonates - *Polycarbonate*

General Information

Product Description

Polycarbonate; MVR (300 °C/1.2 kg) 6.0 cm³/10 min; high viscosity; available in transparent, translucent and opaque colors

Applications

- Extrusion; Injection molding; Food contact quality;

General

| | | | |
|---------------------|---------------------------|---------------------|-----------------|
| Material Status | • Commercial: Active | | |
| Availability | • Africa & Middle East | • Europe | • North America |
| | • Asia Pacific | • Latin America | |
| Features | • Food Contact Acceptable | | |
| Processing Method | • Extrusion | • Injection Molding | |
| Resin ID (ISO 1043) | • PC | | |

Properties ¹

| Physical | Nominal Value | Unit | Test Method |
|---|---------------|--|--------------|
| Density | 1.20 | g/cm ³ | ISO 1183 |
| Melt Volume-Flow Rate (MVR) (300°C/1.2 kg) | 6.0 | cm ³ /10min | ISO 1133 |
| Molding Shrinkage | | | |
| Across Flow ² | 0.60 to 0.80 | % | ISO 2577 |
| Flow ² | 0.60 to 0.80 | % | ISO 2577 |
| Across Flow : 0.0787 in ³ | 0.75 | % | ISO 294-4 |
| Flow : 0.0787 in ³ | 0.70 | % | ISO 294-4 |
| Water Absorption (Saturation, 73°F) | 0.30 | % | ISO 62 |
| Water Absorption (Equilibrium, 73°F, 50% RH) | 0.12 | % | ISO 62 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus | 341000 | psi | ISO 527-1/1 |
| Tensile Stress (Yield) | 9430 | psi | ISO 527-2/50 |
| Tensile Stress (Break) | 10900 | psi | ISO 527-2/50 |
| Tensile Strain (Yield) | 6.3 | % | ISO 527-2/50 |
| Tensile Strain (Break) | 130 | % | ISO 527-2/50 |
| Nominal Tensile Strain at Break | > 50 | % | ISO 527-2/50 |
| Tensile Creep Modulus (1 hr) | 319000 | psi | ISO 899-1 |
| Tensile Creep Modulus (1000 hr) | 276000 | psi | ISO 899-1 |
| Flexural Modulus ⁴ | 341000 | psi | ISO 178 |
| Flexural Stress ⁴ | | | ISO 178 |
| -- | 13900 | psi | |
| 3.5% Strain | 10400 | psi | |
| Flexural Strain at Flexural Strength ⁵ | 7.2 | % | ISO 178 |
| Films | Nominal Value | Unit | Test Method |
| Water Vapor Transmission Rate (73°F, 85% RH, 3.9 mil) | 0.97 | g/100 in ² /24 hr | ISO 15106-1 |
| Gas Permeation | | | ISO 2556 |
| Carbon Dioxide : 1.0 mil | 16900 | cm ³ /m ² /bar/24 hr | |
| Carbon Dioxide : 3.9 mil | 3800 | cm ³ /m ² /bar/24 hr | |
| Nitrogen : 1.0 mil | 510 | cm ³ /m ² /bar/24 hr | |
| Nitrogen : 3.9 mil | 120 | cm ³ /m ² /bar/24 hr | |
| Oxygen : 1.0 mil | 2760 | cm ³ /m ² /bar/24 hr | |
| Oxygen : 3.9 mil | 650 | cm ³ /m ² /bar/24 hr | |



| Impact | Nominal Value | Unit | Test Method |
|---|----------------------|-------------------------------|--------------------|
| Charpy Notched Impact Strength | | | ISO 179/1eA |
| -22°F, 0.118 in, Complete Break | 8.6 | ft·lb/in ² | |
| 73°F, 0.118 in, Partial Break | 38 | ft·lb/in ² | |
| Charpy Unnotched Impact Strength | | | ISO 179/1eU |
| -76°F | No Break | | |
| -22°F | No Break | | |
| 73°F | No Break | | |
| Notched Izod Impact Strength | | | ISO 180/A |
| -22°F, 0.118 in, Complete Break | 9.5 | ft·lb/in ² | |
| 73°F, 0.118 in, Partial Break | 33 | ft·lb/in ² | |
| Multi-Axial Instrumented Impact Energy | | | ISO 6603-2 |
| -22°F | 51.6 | ft·lb | |
| 73°F | 44.3 | ft·lb | |
| Multi-Axial Instrumented Impact Peak Force | | | ISO 6603-2 |
| -22°F | 1460 | lbf | |
| 73°F | 1260 | lbf | |
| Hardness | Nominal Value | Unit | Test Method |
| Ball Indentation Hardness | 16100 | psi | ISO 2039-1 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (66 psi, Unannealed) | 286 | °F | ISO 75-2/B |
| Deflection Temperature Under Load (264 psi, Unannealed) | 264 | °F | ISO 75-2/A |
| Glass Transition Temperature ⁶ | 300 | °F | ISO 11357-2 |
| Vicat Softening Temperature | | | |
| -- | 302 | °F | ISO 306/B120 |
| -- | 300 | °F | ISO 306/B50 |
| CLTE - Flow (73 to 131°F) | 3.6E-5 | in/in/°F | ISO 11359-2 |
| CLTE - Transverse (73 to 131°F) | 3.6E-5 | in/in/°F | ISO 11359-2 |
| Thermal Conductivity | 1.4 | Btu·in/hr/ft ² /°F | ISO 8302 |
| Heat Resistance - Ball Pressure Test | 284 | °F | IEC 60695-10-2 |
| Electrical | Nominal Value | Unit | Test Method |
| Surface Resistivity | 1.0E+16 | ohms | IEC 60093 |
| Surface Resistivity | 1.0E+16 | ohms | IEC 62631-3-2 |
| Volume Resistivity | 1.0E+16 | ohms·cm | IEC 60093 |
| Volume Resistivity | 1.0E+14 | ohms·m | IEC 62631-3-1 |
| Electric Strength (0.0394 in) | 860 | V/mil | IEC 60243-1 |
| Relative Permittivity | | | IEC 60250 |
| 100 Hz | 3.10 | | |
| 1 MHz | 3.00 | | |
| Dissipation Factor | | | IEC 60250 |
| 100 Hz | 5.0E-4 | | |
| 1 MHz | 9.5E-3 | | |
| Comparative Tracking Index | | | IEC 60112 |
| Solution A | 250 | V | |
| Solution B ⁷ | 125 | V | |
| Electrolytic Corrosion | A1 | | IEC 60426 |
| Flammability | Nominal Value | Unit | Test Method |
| Flame Rating | | | UL 94 |
| 0.06 in | HB | | |
| 0.030 in | V-2 | | |
| Glow Wire Flammability Index | | | IEC 60695-2-12 |
| 0.030 in | 1610 | °F | |
| 0.06 in | 1610 | °F | |
| 0.12 in | 1710 | °F | |
| Glow Wire Ignition Temperature | | | IEC 60695-2-13 |
| 0.030 in | 1610 | °F | |
| | 1610 | °F | |
| | 1650 | °F | |
| | 27 | % | ISO |
| 15 f Flame from Small Burner ⁹ (78.7 mil) | K1, F1 | | DIN |



| | | |
|--------------------------------------|---------------------------|--------------------|
| Burning Rate - US-FMVSS (> 39.4 mil) | PASSED | ISO 3795 |
| Flash Ignition Temperature | 896 °F | ASTM D1929 |
| Needle Flame Test | | IEC 60695-11-5 |
| Method F : 59.1 mil | 60 sec | |
| Method F : 78.7 mil | 120 sec | |
| Method F : 0.12 in | 120 sec | |
| Method K : 78.7 mil | 5 sec | |
| Method K : 0.12 in | 10 sec | |
| Self Ignition Temperature | 1022 °F | ASTM D1929 |
| Optical | Nominal Value Unit | Test Method |
| Refractive Index ¹⁰ | 1.586 | ISO 489 |
| Light Transmittance | | ISO 13468-2 |
| 39.37 mil | 89.0 % | |
| 78.74 mil | 89.0 % | |
| 118.1 mil | 88.0 % | |
| 157.5 mil | 87.0 % | |
| Haze (118.1 mil) | < 0.800 % | ISO 14782 |
| Additional Information | Nominal Value Unit | Test Method |
| Test Specimen Production | | ISO 294 |
| Inj. Molding - Injection Velocity | 472 in/min | |
| Inj. Molding - Melt Temperature | 572 °F | |
| Inj. Molding - Mold Temperature | 194 °F | |

Processing Information

| | Nominal Value | Unit |
|---------------------------------------|------------------|--------|
| Injection | | |
| Drying Temperature - Dry Air Dryer | 248 | °F |
| Drying Time - Dry Air Dryer | 2.0 to 3.0 | hr |
| Suggested Max Moisture | < 0.020 | % |
| Suggested Shot Size | 30 to 70 | % |
| Rear Temperature | 500 to 518 | °F |
| Middle Temperature | 536 to 554 | °F |
| Front Temperature | 554 to 572 | °F |
| Nozzle Temperature | 572 to 590 | °F |
| Melt Temperature (Optimum) | 590 | °F |
| Mold Temperature | 176 to 248 | °F |
| Back Pressure | 725 to 2180 | psi |
| Vent Depth | 9.8E-4 to 3.0E-3 | in |
| Holding Pressure - % of Inj. Pressure | 50 to 75 | % |
| Peripheral Screw Speed | 2 to 8 | in/sec |

Notes

¹ Typical properties: these are not to be construed as specifications.

² Value range based on general practical experience

³ 60×60×2 mm; 500 bar

⁴ 0.079 in/min

⁵ 2.0 mm/min

⁶ 10°C/min

⁷ CTI M

⁸ Procedure A

⁹ Method K and F

¹⁰ Method A

