

Makrolon® ET UV110

Covestro - Polycarbonates - *Polycarbonate*

General Information

Product Description

PC/UV absorber concentrate; high viscosity; easy release; special grade for the coextrusion of Makrolon ET base resins; available in color code 550054 only; solid sheet; multi wall sheets / profiles

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Mold Release	• High Viscosity	
Uses	• Plastics Modification	• Profiles	• Sheet
RoHS Compliance	• RoHS Compliant		
Processing Method	• Coextrusion	• Extrusion	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.19	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	10	cm ³ /10min	ISO 1133
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (73°F)	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	266	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	244	°F	ISO 75-2/A
Vicat Softening Temperature	277	°F	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity (73°F)	1.0E+16	ohms·cm	IEC 60093

Notes

¹ Typical properties: these are not to be construed as specifications.

