

Makrolon® ET UV120

 Covestro - Polycarbonates - *Polycarbonate*
General Information
Product Description

PC/UV absorber concentrate; high viscosity; easy release; special grade for the coextrusion of Makrolon ET base resins; available in color code 451105 only; solid sheet; multi wall sheets / profiles

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Features	• Good Mold Release • High Viscosity		
Uses	• Plastics Modification	• Profiles	• Sheet
RoHS Compliance	• RoHS Compliant		
Processing Method	• Coextrusion	• Extrusion	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.19	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	11	cm ³ /10min	ISO 1133
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (73°F)	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	262	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	241	°F	ISO 75-2/A
Vicat Softening Temperature	273	°F	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity (73°F)	1.0E+16	ohms·cm	IEC 60093

Notes
¹ Typical properties: these are not to be construed as specifications.
