

Makrolon® M430 GF

 Covestro - Polycarbonates - *Polycarbonate*
General Information
Product Description

polycarbonate; MVR (300 °C/1.2 kg) 7.0 cm³/10 min; low viscosity; 30 % glass fiber reinforced; biocompatible according to many ISO 10993-1 test requirements; injection molding; available in opaque colors only; suitable for medical devices

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Features	• Biocompatible	• Low Viscosity	
Uses	• Medical Devices	• Medical/Healthcare Applications	
Agency Ratings	• ISO 10993-1	• USP Class VI	
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Opaque	
Processing Method	• Injection Molding		
ISO Designation	• PC-GF30		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.42	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	7.0	cm³/10min	ISO 1133
Molding Shrinkage ²			ISO 294-4
Across Flow : 0.0787 in	0.50	%	
Flow : 0.0787 in	0.20	%	
Water Absorption (Saturation, 73°F)	0.26	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.10	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	1.16E+6	psi	ISO 527-1/1
Tensile Stress (Break, 73°F)	18600	psi	ISO 527-2/5
Tensile Strain (Break, 73°F)	2.8	%	ISO 527-2/5
Flexural Modulus ³ (73°F)	1.17E+6	psi	ISO 178
Flexural Stress ³ (73°F)	28600	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ⁴			ISO 180/A
-22°F	6.2	ft·lb/in²	
73°F	6.7	ft·lb/in²	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	291	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	284	°F	ISO 75-2/A
Vicat Softening Temperature	300	°F	ISO 306/B120
CLTE - Flow (73 to 131°F)	1.1E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F)	2.2E-5	in/in/°F	ISO 11359-2
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (572°F, 1000 sec ⁻¹)	380	Pa·s	ISO 11443-A

Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Dry Air Dryer	248	°F



Drying Time - Dry Air Dryer	4.0 hr
Processing (Melt) Temp	572 °F
Mold Temperature	212 °F

Notes

¹ Typical properties: these are not to be construed as specifications.

² 60x60x2mm

³ 0.079 in/min

⁴ 3.0 mm

