

TAIRILITE® AC2854

 Formosa Chemicals & Fibre Corporation - *Polycarbonate*

General Information

Product Description

Diffusion

Features: Light diffusion, Mid flow, UV resistance.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Features	• Good Light Diffusion • Medium Flow • UV Resistant
Agency Ratings	• EC 1907/2006 (REACH)
RoHS Compliance	• RoHS Compliant
UL File Number	• E162823

 Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity ²	1.20		ASTM D792
Density (73°F)	1.20	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	12	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	12	g/10 min	ISO 1133
Molding Shrinkage - Flow (0.126 in)	5.0E-3 to 7.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ³ (73°F)	10100	psi	ASTM D638
Tensile Stress (73°F)	10200	psi	ISO 527-2/50
Flexural Modulus ⁴ (73°F)	313000	psi	ASTM D790
Flexural Modulus ⁴ (73°F)	313000	psi	ISO 178
Flexural Strength ⁴ (73°F)	15600	psi	ASTM D790
Flexural Stress ⁴ (73°F)	15700	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F, 0.157 in)	33	ft·lb/in ²	ISO 179
Unnotched Izod Impact (73°F, 0.126 in)	14	ft·lb/in	ASTM D4812
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 73°F)	122		ASTM D785
Rockwell Hardness (R-Scale, 73°F)	122		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ⁵ (264 psi, Unannealed, 0.126 in)	262	°F	ASTM D648
Deflection Temperature Under Load ⁵ (264 psi, Unannealed, 0.157 in)	262	°F	ISO 75-2/A
RTI Elec	248 to 266	°F	UL 746B
RTI Imp	248 to 266	°F	UL 746B
RTI Str	248 to 266	°F	UL 746B
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.030 in)	V-2		UL 94
Optical	Nominal Value	Unit	Test Method
Light Transmittance (126.0 mil)	45.0 to 80.0	%	ASTM D1003
Haze (126.0 mil)	88.0 to 91.0	%	ASTM D1003

