

Plaslube® PC-50/SI/20 NAT

 Techmer Polymer Modifiers - *Polycarbonate*
General Information
General

Material Status	• Commercial: Active
Availability	• North America
Appearance	• Natural Color
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	5500	psi	ASTM D638
Tensile Stress (Yield)	6670	psi	ISO 527-2
Tensile Elongation (Break)	4.7	%	ASTM D638
Flexural Modulus	153000	psi	ASTM D790
Flexural Modulus	537000	psi	ISO 178
Flexural Strength	6300	psi	ASTM D790
Flexural Stress	11800	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
0.125 in	0.80	ft·lb/in	ASTM D256
0.125 in	0.75	ft·lb/in	ISO 180

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	250	°F
Drying Time	3.0 to 4.0	hr
Rear Temperature	500 to 540	°F
Middle Temperature	510 to 550	°F
Front Temperature	520 to 560	°F
Nozzle Temperature	530 to 570	°F
Processing (Melt) Temp	510 to 565	°F
Mold Temperature	125 to 200	°F
Injection Rate	Slow-Moderate	
Back Pressure	0.00 to 50.0	psi
Screw Speed	Slow	

Notes
¹ Typical properties: these are not to be construed as specifications.
