

Plaslube® PC-50/TF/15 BK223

 Techmer Polymer Modifiers - *Polycarbonate*
General Information
General

Material Status	• Commercial: Active
Availability	• North America
Appearance	• Black
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.28	g/cm ³	
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	9.7	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	7000	psi	ASTM D638
Tensile Elongation (Break)	74	%	ASTM D638
Flexural Modulus	339000	psi	ASTM D790
Flexural Strength	11500	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	2.8	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	256	°F	ASTM D648

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	250	°F
Drying Time	3.0 to 4.0	hr
Rear Temperature	500 to 540	°F
Middle Temperature	510 to 550	°F
Front Temperature	520 to 560	°F
Nozzle Temperature	530 to 570	°F
Processing (Melt) Temp	510 to 565	°F
Mold Temperature	125 to 200	°F
Injection Rate	Slow-Moderate	
Back Pressure	0.00 to 50.0	psi
Screw Speed	Slow	

Notes

¹ Typical properties: these are not to be construed as specifications.

