

TES J-50/20

 Techmer Polymer Modifiers - *Polycarbonate*
General Information

General			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight		
Features	• Creep Resistant	• Good Dimensional Stability	• High Strength
	• Fatigue Resistant	• High Heat Resistance	
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.35		ASTM D792
Molding Shrinkage - Flow (0.125 in)	3.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	900000	psi	ASTM D638
Tensile Strength (Break, 73°F)	16000	psi	ASTM D638
Tensile Elongation (Break, 73°F)	3.0	%	ASTM D638
Flexural Modulus (73°F)	800000	psi	ASTM D790
Flexural Strength (Break, 73°F)	22000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.250 in)	2.5	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	80		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	305	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	290	°F	ASTM D648
RTI Elec			UL 746B
0.06 in	167	°F	
0.12 in	167	°F	
RTI Imp			UL 746B
0.06 in	167	°F	
0.12 in	167	°F	
RTI Str			UL 746B
0.06 in	167	°F	
0.12 in	167	°F	
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.06 in	V-2		
0.12 in	V-0		

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	250	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.10	%



Rear Temperature	570 to 600 °F
Middle Temperature	590 to 650 °F
Front Temperature	600 to 630 °F
Nozzle Temperature	590 to 630 °F
Processing (Melt) Temp	580 to 625 °F
Mold Temperature	160 to 190 °F

Notes

¹ Typical properties: these are not to be construed as specifications.

