

TES J-50/30/TF/15 BK3585

 Techmer Polymer Modifiers - *Polycarbonate*
General Information
General

Material Status	<ul style="list-style-type: none"> Commercial: Active 		
Availability	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific 	<ul style="list-style-type: none"> Europe Latin America 	<ul style="list-style-type: none"> North America
RoHS Compliance	<ul style="list-style-type: none"> RoHS Compliant 		
Forms	<ul style="list-style-type: none"> Pellets 		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.57		ASTM D792
Molding Shrinkage - Flow (0.125 in)	2.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.080	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	17000	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	1.10E+6	psi	ASTM D790
Flexural Strength	24000	psi	ASTM D790
Compressive Strength	16000	psi	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	3.3	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	115		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	295	°F	ASTM D648
CLTE - Flow	1.5E-5	in/in/°F	ASTM D696
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-1		UL 94

Notes
¹ Typical properties: these are not to be construed as specifications.
