

**TRIREX® Compound HS3022G30**

Samyang Corporation - Polycarbonate

## General Information

**Product Description**

Polycarbonates provides excellent mechanical properties, dimensional stability, and good electrical property. Widely used in various industrial fields such as electronics, automobiles.

**General**

|                 |   |
|-----------------|---|
| Material Status | • Commercial: Active                    |
| Availability    | • Asia Pacific • Europe • North America |
| Uses            | • Electrical/Electronic Applications    |

 Properties <sup>1</sup>

|   | Nominal Value    | Unit     | Test Method |
|---|------------------|----------|-------------|
| <b>Physical</b>   |                  |          |             |
| Density / Specific Gravity                              | 1.35             |          | ASTM D792   |
| Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)                | 1.0              | g/10 min | ASTM D1238  |
| Molding Shrinkage - Flow (0.118 in)                     | 1.0E-3 to 3.0E-3 | in/in    | ASTM D955   |
| Water Absorption (24 hr, 73°F)                          | 0.12             | %        | ASTM D570   |
| <b>Mechanical</b>                                       |                  |          |             |
| Tensile Strength (Yield)                                | 14200            | psi      | ASTM D638   |
| Tensile Elongation (Yield)                              | 3.0              | %        | ASTM D638   |
| Flexural Modulus  | 925000           | psi      | ASTM D790   |
| Flexural Strength (Yield)                               | 21300            | psi      | ASTM D790   |
| <b>Impact</b>   |                  |          |             |
| Notched Izod Impact (73°F)                              | 2.8              | ft-lb/in | ASTM D256   |
| <b>Hardness</b>   |                  |          |             |
| Rockwell Hardness                                       | 122              |          | ASTM D785   |
| <b>Thermal</b>  |                  |          |             |
| Deflection Temperature Under Load (264 psi, Unannealed) | 259              | °F       | ASTM D648   |
| CLTE - Flow   | 1.3E-6           | in/in/°F | ASTM D696   |
| <b>Electrical</b>                                       |                  |          |             |
| Volume Resistivity                                      | 4.0E+16          | ohms·cm  | ASTM D257   |
| Dielectric Strength                                     | 480              | V/mil    | ASTM D149   |
| Dielectric Constant                                     | 3.11             |          | ASTM D150   |
| Dissipation Factor                                      | 9.7E-3           |          | ASTM D150   |
| Arc Resistance  | 120              | sec      | ASTM D495   |
| <b>Flammability</b>                                     |                  |          |             |
| Flame Rating (0.030 in)                                 | HB               |          | UL 94       |

