

TRIREX® Compound NH3022PN3

Samyang Corporation - Polycarbonate

General Information
Product Description

Polycarbonates provides excellent mechanical properties, dimensional stability, and good electrical property. Widely used in various industrial fields such as electronics, automobiles.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Uses	• Electrical/Electronic Applications • Television Housings		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.20		ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	27	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.118 in)	5.0E-3 to 7.0E-3	in/in	ASTM D955
Water Absorption (24 hr, 73°F)	0.13	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	9960	psi	ASTM D638
Tensile Elongation (Yield)	160	%	ASTM D638
Flexural Modulus	356000	psi	ASTM D790
Flexural Strength (Yield)	14200	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	1.1	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	226	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.08 in)	V-0		UL 94

