

TRIREX® Compound SM3-3025H

Samyang Corporation - Polycarbonate

General Information

Product Description

Si-PC (Siloxane PC) is as polycarbonate-polysiloxane copolymer, having excellent low temperature ductility, impact toughness and chemical resistance.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Uses	• Cell Phones	• Electrical/Electronic Applications	• Television Housings

 Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.20		ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.118 in)	5.0E-3 to 7.0E-3	in/in	ASTM D955
Water Absorption (24 hr, 73°F)	0.15	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	9250	psi	ASTM D638
Tensile Elongation (Yield)	100	%	ASTM D638
Flexural Modulus	299000	psi	ASTM D790
Flexural Strength (Yield)	12500	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	15	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness	120		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	270	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.03 in)	V-2		UL 94

Notes

¹ Typical properties: these are not to be construed as specifications.

