

## AuroraGuard™ 3512LGU

Aurora Material Solutions, LLC - Polycarbonate + ABS

### General Information

#### Product Description

General Purpose PC/ABS Alloy with UV

Formerly known as EnValoy 3512LGU

#### General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Additive	• UV Stabilizer		
Features	• General Purpose	• UV Stabilized	
Uses	• Lawn & Garden Equipment		
Appearance	• Black	• Colors Available	• Natural Color
Processing Method	• Injection Molding		

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.12		ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	40	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.126 in)	5.0E-3 to 7.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	7400	psi	ASTM D638
Tensile Elongation (Break)	50	%	ASTM D638
Flexural Modulus	305000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	8.0	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	215	°F	ASTM D648

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	220	°F
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.020	%
Rear Temperature	460 to 490	°F
Middle Temperature	470 to 500	°F
Front Temperature	480 to 510	°F
Nozzle Temperature	480 to 520	°F
Processing (Melt) Temp	460 to 520	°F
Mold Temperature	90 to 180	°F
Back Pressure	30.0 to 70.0	psi

#### Injection Notes

Maximum Drying Time 8.0 hrs

