

## AuroraGuard™ ENV15-78012

Aurora Material Solutions, LLC - Polycarbonate + ABS

### General Information

#### Product Description

AuroraGuard™ ENV15-78012 is a Hydrolytically Stable, Black, Polycarbonate/Acrylonitrile Butadiene Styrene (PC/ABS) Injection Molding Grade.

Formerly branded as ENVIROLOY®

#### General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Hydrolytically Stable		
Uses	• Automotive Interior Parts • Electrical Parts	• Electrical/Electronic Applications • General Purpose	
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• PC/ABS		

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.14		ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	22	g/10 min	ASTM D1238
Molding Shrinkage - Flow	5.0E-3 to 7.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	7850	psi	ASTM D638
Tensile Elongation (Break)	75	%	ASTM D638
Flexural Modulus	335000	psi	ASTM D790
Flexural Strength	12500	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	12	ft·lb/in	ASTM D256
Gardner Impact <sup>2</sup>	440	in·lb	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	262	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	225	°F	ASTM D648
Vicat Softening Temperature	258	°F	ASTM D1525 <sup>3</sup>
Flammability	Nominal Value	Unit	Test Method
Burning Rate (0.125 in, Self-Extinguishing)	0.0	in/min	ISO 3795
Flame Rating (0.06 in)	HB		UL 94

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	185 to 225	°F
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.020	%
Rear Temperature	460 to 510	°F
Middle Temperature	480 to 550	°F
Front Temperature	480 to 550	°F
Nozzle Temperature	480 to 520	°F



Mold Temperature	150 to 190 °F
Injection Rate	Moderate-Fast
Back Pressure	50.0 to 100 psi
Screw Speed	40 to 70 rpm

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> No Failure Energy

<sup>3</sup> Rate B (120°C/h), Loading 2 (50 N)

