

AuroraGuard™ 10TF801

 Aurora Material Solutions, LLC - *Polycarbonate + ABS*
General Information
Product Description

Talc-filled PC/ABS, increased HDT, increased stiffness

Formerly known as EnValoy 10TF801

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Talc, 10% Filler by Weight		
Features	• Good Stiffness		
Uses	• Automotive Applications	• Business Equipment	
Appearance	• Black	• Colors Available	• Natural Color
Processing Method	• Injection Molding		

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.24		ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	8.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.126 in)	4.0E-3	in/in	ASTM D955
Mechanical			
Tensile Strength (Yield)	8500	psi	ASTM D638
Tensile Elongation (Break)	> 4.0	%	ASTM D638
Flexural Modulus	573000	psi	ASTM D790
Flexural Strength	13800	psi	ASTM D790
Impact			
Notched Izod Impact (73°F)	1.2	ft-lb/in	ASTM D256
Thermal			
Deflection Temperature Under Load (66 psi, Unannealed)	240	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	210	°F	ASTM D648

Processing Information

	Nominal Value	Unit
Injection		
Drying Temperature	180 to 220	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.020	%
Rear Temperature	450 to 500	°F
Middle Temperature	470 to 510	°F
Front Temperature	465 to 525	°F
Nozzle Temperature	475 to 525	°F
Processing (Melt) Temp	475 to 525	°F
Mold Temperature	140 to 190	°F
Back Pressure	25.0 to 100	psi
Screw Speed	25 to 75	rpm

Injection Notes

Maximum Drying Time 4.0 hrs

