

AuroraGuard™ 2412UR

Aurora Material Solutions, LLC - Polycarbonate + ABS

General Information

Product Description

Injection Grade PC/ABS with UV Stabilizer and Mold Release

Formerly known as EnValoy 2412UR

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Additive	• Mold Release	• UV Stabilizer	
Features	• Good Mold Release	• UV Stabilized	
Uses	• Appliances	• Electrical/Electronic Applications	
Appearance	• Black	• Colors Available	• Natural Color
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.14		ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	26	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.126 in)	6.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	8350	psi	ASTM D638
Tensile Elongation (Break)	> 140	%	ASTM D638
Flexural Modulus	329000	psi	ASTM D790
Flexural Strength	12500	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	12	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	230	°F	ASTM D648

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	200 to 210	°F
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.020	%
Rear Temperature	480 to 520	°F
Middle Temperature	490 to 520	°F
Front Temperature	490 to 530	°F
Nozzle Temperature	480 to 520	°F
Processing (Melt) Temp	480 to 520	°F
Mold Temperature	140 to 200	°F

Injection Notes

Maximum Drying Time 4.0 hrs

