

AuroraGuard™ ENV15-NC260

Aurora Material Solutions, LLC - Polycarbonate + ABS

General Information
Product Description

Injection Molding Grade, High Impact and Ductility at Cold Temperature,
Interior Automotive Trim Applications, RoHS Compliant
NC260 = To Be Assigned 5 Digit Number Indicating Natural, Black, or Custom Color.
The ENV15 Series Products Are Available With Mold Release and/or UV Stabilizer.

Formerly known as ENVIROLOY® ENV15-NC260

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Features	• Ductile	• High Impact Resistance	• Low Temperature Impact Resistance
Uses	• Automotive Interior Parts	• Electronic Displays	• Recreational Vehicle Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Black	• Colors Available	• Natural Color
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.14		ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	22	g/10 min	ASTM D1238
Molding Shrinkage - Flow	5.0E-3 to 7.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	7900	psi	ASTM D638
Tensile Elongation (Break)	> 100	%	ASTM D638
Flexural Modulus	332000	psi	ASTM D790
Flexural Strength	12700	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-22°F	8.0	ft·lb/in	
73°F	12	ft·lb/in	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	225	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Burning Rate (Self-Extinguishing)	< 1.6	in/min	FMVSS 302

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180 to 220	°F
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.050	%
Rear Temperature	490 to 560	°F
Middle Temperature	490 to 560	°F
Front Temperature	510 to 580	°F
Nozzle Temperature	525 to 585	°F
Mold Temperature	140 to 180	°F



Injection Rate	Moderate-Fast
Back Pressure	50.0 to 100 psi
Screw Speed	40 to 70 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

