

Bayblend® FR3008

 Covestro - Polycarbonates - *Polycarbonate + ABS*
General Information
Product Description

(PC+ABS)-Blend; flame retardant; Vicat/B 120 temperature = 103°C; improved chemical and very good hydrolysis resistance; HDT/A >= 85°C; UL recognition 94 V-0 at 1.5 mm; glow wire temperature (GWFI): 960°C at 2.0 mm; good light stability

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• Flame Retardant		
Features	• Chemical Resistant • Flame Retardant	• Hydrolysis Resistant • Light Stabilized	
RoHS Compliance	• RoHS Compliant		
ISO Designation	• PC+ABS-FR(40)		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.18	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (240°C/5.0 kg)	13	cm ³ /10min	ISO 1133
Molding Shrinkage ²			ISO 2577
Across Flow : 464°F, 0.118 in	0.50 to 0.70	%	
Flow : 464°F, 0.118 in	0.50 to 0.70	%	
Water Absorption (Saturation, 73°F)	0.50	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	406000	psi	ISO 527-1/1
Tensile Stress (Yield, 73°F)	8700	psi	ISO 527-2/50
Tensile Stress (Break, 73°F)	7250	psi	ISO 527-2/50
Tensile Strain (Yield, 73°F)	4.0	%	ISO 527-2/50
Tensile Strain (Break, 73°F)	> 50	%	ISO 527-2/50
Flexural Modulus ³ (73°F)	392000	psi	ISO 178
Flexural Stress ³ (73°F)	14200	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/A
-22°F	4.8	ft-lb/in ²	
73°F	14	ft-lb/in ²	
Unnotched Izod Impact Strength (73°F)	No Break		ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	203	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	185	°F	ISO 75-2/A
Vicat Softening Temperature			
--	217	°F	ISO 306/B120
--	214	°F	ISO 306/B50
CLTE - Flow (73 to 131°F)	4.2E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F)	4.4E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity (73°F)	1.0E+16	ohms-cm	IEC 60093
Electric Strength (73°F, 0.0394 in)	760	V/mil	IEC 60243-1



Relative Permittivity		IEC 60250
73°F, 100 Hz	3.20	
73°F, 1 MHz	3.10	
Dissipation Factor		IEC 60250
73°F, 100 Hz	5.0E-3	
73°F, 1 MHz	7.0E-3	
Comparative Tracking Index (Solution A)	300 V	IEC 60112
Flammability	Nominal Value	Unit
Flame Rating		UL 94
0.06 in	V-0	
0.08 in	5VB	
0.12 in	5VA	
Glow Wire Flammability Index (0.08 in)	1760 °F	IEC 60695-2-12
Oxygen Index ⁴	32 %	ISO 4589-2
Fill Analysis	Nominal Value	Unit
Melt Viscosity ⁵ (500°F)	195 Pa·s	ISO 11443-A

Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Dry Air Dryer	176	°F
Drying Time - Dry Air Dryer	4.0	hr
Suggested Max Moisture	< 0.020	%
Suggested Shot Size	30 to 70	%
Rear Temperature	428 to 446	°F
Middle Temperature	437 to 455	°F
Front Temperature	446 to 464	°F
Nozzle Temperature	491 to 509	°F
Processing (Melt) Temp	464 to 518	°F
Mold Temperature	140 to 194	°F
Back Pressure	725 to 2180	psi
Vent Depth	9.8E-4 to 3.0E-3	in

Injection Notes

Standard Melt Temperature: 260°C
Peripheral Screw Speed: 0.05 - 0.2 m/s
Hold Pressure (% of Injection Pressure): 50 - 75%

Notes

¹ Typical properties: these are not to be construed as specifications.

² 150x105x3mm., MT 80°C

³ 0.079 in/min

⁴ Procedure A

⁵ 1000s-1

