

Bayblend® FR3110 TV

 Covestro - Polycarbonates - *Polycarbonate + ABS*
General Information
Product Description

(PC+ABS)-Blend; flame retardant; easy flowing; Vicat/B 120 temperature = 110°C; increased heat resistance; UL recognition 94 V-0 at 1.5 mm

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Additive	• Flame Retardant		
Features	• Flame Retardant	• Good Flow	• High Heat Resistance
RoHS Compliance	• RoHS Compliant		
ISO Designation	• PC+ABS-FR(40)		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.18	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (240°C/5.0 kg)	29	cm ³ /10min	ISO 1133
Molding Shrinkage ²			ISO 2577
Across Flow : 464°F, 0.118 in	0.50 to 0.70	%	
Flow : 464°F, 0.118 in	0.50 to 0.70	%	
Water Absorption (Saturation, 73°F)	0.50	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	377000	psi	ISO 527-1/1
Tensile Stress (Yield, 73°F)	8700	psi	ISO 527-2/50
Tensile Stress (Break, 73°F)	7250	psi	ISO 527-2/50
Tensile Strain (Yield, 73°F)	4.0	%	ISO 527-2/50
Tensile Strain (Break, 73°F)	> 50	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (73°F)	5.7	ft·lb/in ²	ISO 180/A
Unnotched Izod Impact Strength (73°F)	No Break		ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	214	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	196	°F	ISO 75-2/A
Vicat Softening Temperature			
--	230	°F	ISO 306/B120
--	226	°F	ISO 306/B50
CLTE - Flow (73 to 131°F)	3.8E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F)	3.8E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity (73°F)	1.0E+16	ohms·cm	IEC 60093
Electric Strength (73°F, 0.0394 in)	760	V/mil	IEC 60243-1
Relative Permittivity			IEC 60250
73°F, 100 Hz	3.20		
73°F, 1 MHz	3.10		
Dissipation Factor			IEC 60250
73°F, 100 Hz	5.0E-3		



73°F, 1 MHz	7.0E-3	
Comparative Tracking Index (Solution A)	350 V	IEC 60112
Flammability	Nominal Value Unit	Test Method
Flame Rating (0.06 in)	V-0	UL 94
Fill Analysis	Nominal Value Unit	Test Method
Melt Viscosity ³ (500°F)	140 Pa·s	ISO 11443-A

Processing Information

Injection	Nominal Value Unit
Drying Temperature - Dry Air Dryer	176 °F
Drying Time - Dry Air Dryer	4.0 hr
Suggested Max Moisture	< 0.020 %
Suggested Shot Size	30 to 70 %
Rear Temperature	428 to 446 °F
Middle Temperature	437 to 455 °F
Front Temperature	446 to 464 °F
Nozzle Temperature	491 to 509 °F
Processing (Melt) Temp	464 to 536 °F
Mold Temperature	140 to 194 °F
Back Pressure	725 to 2180 psi
Vent Depth	9.8E-4 to 3.0E-3 in

Injection Notes

Standard Melt Temperature: 260°C
 Hold Pressure (% of Injection Pressure): 50 - 75%
 Peripheral Screw Speed: 0.05 - 0.2 m/s

Notes

¹ Typical properties: these are not to be construed as specifications.

² 150x105x3mm,, MT 80°C

³ 1000s-1

