

Bayblend® T65 PG

Covestro - Polycarbonates - *Polycarbonate + ABS*

General Information

Product Description

(PC+ABS)-Blend; Vicat/B 120 temperature = 120°C; easy flowing; good heat resistance; for electroplating applications

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Features	• Good Flow	• High Heat Resistance	• Platable
RoHS Compliance	• RoHS Compliant		
ISO Designation	• PC+ABS		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.13	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (260°C/5.0 kg)	18	cm ³ /10min	ISO 1133
Molding Shrinkage ²			ISO 2577
Across Flow : 500°F, 0.118 in	0.50 to 0.70	%	
Flow : 500°F, 0.118 in	0.50 to 0.70	%	
Water Absorption (Saturation, 73°F)	0.70	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	348000	psi	ISO 527-1/1
Tensile Stress (Yield, 73°F)	7830	psi	ISO 527-2/50
Tensile Stress (Break, 73°F)	6820	psi	ISO 527-2/50
Tensile Strain (Yield, 73°F)	4.4	%	ISO 527-2/50
Tensile Strain (Break, 73°F)	> 50	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/A
-22°F	17	ft·lb/in ²	
73°F	21	ft·lb/in ²	
Unnotched Izod Impact Strength			ISO 180
-22°F	No Break		
73°F	No Break		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	252	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	216	°F	ISO 75-2/A
Vicat Softening Temperature			
--	248	°F	ISO 306/B120
--	244	°F	ISO 306/B50
CLTE - Flow (73 to 131°F)	4.4E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F)	4.7E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity (73°F)	1.0E+16	ohms·cm	IEC 60093
Electric Strength (73°F, 0.0394 in)	890	V/mil	IEC 60243-1
Relative Permittivity			IEC 60250
73°F, 100 Hz	3.10		
73°F, 1 MHz	3.00		



Dissipation Factor		IEC 60250
73°F, 100 Hz	3.0E-3	
73°F, 1 MHz	8.5E-3	
Comparative Tracking Index (Solution A)	250 V	IEC 60112
Flammability	Nominal Value Unit	Test Method
Flame Rating (0.03 in, Internal Test)	HB	UL 94
Fill Analysis	Nominal Value Unit	Test Method
Melt Viscosity ³ (500°F)	200 Pa·s	ISO 11443-A

Processing Information

Injection	Nominal Value Unit
Drying Temperature - Dry Air Dryer	203 to 230 °F
Drying Time - Dry Air Dryer	4.0 hr
Suggested Max Moisture	< 0.020 %
Suggested Shot Size	30 to 70 %
Rear Temperature	428 to 446 °F
Middle Temperature	437 to 455 °F
Front Temperature	446 to 464 °F
Nozzle Temperature	491 to 509 °F
Processing (Melt) Temp	464 to 518 °F
Mold Temperature	158 to 194 °F
Back Pressure	725 to 2180 psi
Vent Depth	9.8E-4 to 3.0E-3 in

Injection Notes

Standard Melt Temperature: 260°C
Peripheral Screw Speed: 0.05 - 0.2 m/s
Hold Pressure (% of Injection Pressure): 50 - 75%

Notes

¹ Typical properties: these are not to be construed as specifications.

² 150x105x3mm,, MT 80°C

³ 1000s-1

