

Bayblend® T40 LG

Covestro - Polycarbonates - *Polycarbonate + ABS*

General Information

Product Description

ABS+PC-Blend; Vicat/B 120 temperature = 112 °C; easy flowing; improved UV resistance

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Features	• Good Flow	• UV Resistant	
RoHS Compliance	• RoHS Compliant		
ISO Designation	• ABS+PC		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.11	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (260°C/5.0 kg)	14	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow : 500°F, 0.0787 in	0.50 to 0.70	%	
Flow : 500°F, 0.0787 in	0.50 to 0.70	%	
Water Absorption (Saturation, 73°F)	0.70	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	312000	psi	ISO 527-1/1
Tensile Stress (Yield, 73°F)	7250	psi	ISO 527-2/50
Tensile Stress (Break, 73°F)	6240	psi	ISO 527-2/50
Tensile Strain (Yield, 73°F)	3.7	%	ISO 527-2/50
Tensile Strain (Break, 73°F)	> 50	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/A
-22°F	20	ft·lb/in ²	
73°F	26	ft·lb/in ²	
Unnotched Izod Impact Strength			ISO 180
-22°F	No Break		
73°F	No Break		
Multi-Axial Instrumented Impact Energy			ISO 6603-2
-22°F	29.5	ft·lb	
73°F	29.5	ft·lb	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	234	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	203	°F	ISO 75-2/A
Vicat Softening Temperature			
--	234	°F	ISO 306/B120
--	230	°F	ISO 306/B50
CLTE - Flow (73 to 131°F)	4.4E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F)	4.4E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity (73°F)	1.0E+16	ohms·cm	IEC 60093
Electric Strength (73°F, 0.0394 in)	890	V/mil	IEC 60243-1



Relative Permittivity		IEC 60250
73°F, 100 Hz	3.00	
73°F, 1 MHz	2.90	
Dissipation Factor		IEC 60250
73°F, 100 Hz	1.0E-3	
73°F, 1 MHz	9.0E-3	
Comparative Tracking Index (Solution A)	325 V	IEC 60112
Flammability	Nominal Value	Unit
Flame Rating (0.03 in, Internal Test)	HB	UL 94
Fill Analysis	Nominal Value	Unit
Melt Viscosity (500°F, 1000 sec ⁻¹)	185 Pa·s	ISO 11443-A

Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Dry Air Dryer	203 to 230	°F
Drying Time - Dry Air Dryer	4.0	hr
Suggested Max Moisture	< 0.020	%
Suggested Shot Size	30 to 70	%
Rear Temperature	446 to 464	°F
Middle Temperature	455 to 473	°F
Front Temperature	464 to 518	°F
Nozzle Temperature	509 to 527	°F
Processing (Melt) Temp	500 to 536	°F
Mold Temperature	158 to 194	°F
Back Pressure	725 to 2180	psi
Vent Depth	9.8E-4 to 3.0E-3	in
Injection Notes		
Standard Melt Temperature: 270°C		
Peripheral Screw Speed: 0.05 - 0.2 m/s		
Hold Pressure (% of Injection Pressure): 50 - 75%		

Notes

¹ Typical properties: these are not to be construed as specifications.

