

Bayblend® FR3010 IF

Covestro - Polycarbonates - *Polycarbonate + ABS*

General Information

Product Description

(PC+ABS)-Blend; flame retardant; Vicat/B 120 temperature = 108°C; increased heat resistance; UL recognition 94 5VB (1.5 mm); glow wire temperature (GWFI): 960°C at 2.0 mm

General

| | | | |
|-----------------|------------------------|------------------------|-----------------|
| Material Status | • Commercial: Active | | |
| Availability | • Africa & Middle East | • Europe | • North America |
| | • Asia Pacific | • Latin America | |
| Additive | • Flame Retardant | | |
| Features | • Flame Retardant | • High Heat Resistance | |
| RoHS Compliance | • RoHS Compliant | | |
| ISO Designation | • PC+ABS-FR(40) | | |

Properties ¹

| Physical | Nominal Value | Unit | Test Method |
|---|---------------|------------------------|--------------|
| Density (73°F) | 1.18 | g/cm ³ | ISO 1183 |
| Melt Volume-Flow Rate (MVR) (240°C/5.0 kg) | 17 | cm ³ /10min | ISO 1133 |
| Molding Shrinkage ² | | | ISO 2577 |
| Across Flow : 464°F, 0.118 in | 0.50 to 0.70 | % | |
| Flow : 464°F, 0.118 in | 0.50 to 0.70 | % | |
| Water Absorption (Saturation, 73°F) | 0.50 | % | ISO 62 |
| Water Absorption (Equilibrium, 73°F, 50% RH) | 0.20 | % | ISO 62 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus (73°F) | 392000 | psi | ISO 527-1/1 |
| Tensile Stress (Yield, 73°F) | 8700 | psi | ISO 527-2/50 |
| Tensile Stress (Break, 73°F) | 7250 | psi | ISO 527-2/50 |
| Tensile Strain (Yield, 73°F) | 4.0 | % | ISO 527-2/50 |
| Tensile Strain (Break, 73°F) | > 50 | % | ISO 527-2/50 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact Strength (73°F) | 12 | ft·lb/in ² | ISO 180/A |
| Unnotched Izod Impact Strength (73°F) | No Break | | ISO 180 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (66 psi, Unannealed) | 208 | °F | ISO 75-2/B |
| Deflection Temperature Under Load (264 psi, Unannealed) | 190 | °F | ISO 75-2/A |
| Vicat Softening Temperature | | | |
| -- | 226 | °F | ISO 306/B120 |
| -- | 223 | °F | ISO 306/B50 |
| CLTE - Flow (73 to 131°F) | 4.2E-5 | in/in/°F | ISO 11359-2 |
| CLTE - Transverse (73 to 131°F) | 4.4E-5 | in/in/°F | ISO 11359-2 |
| Flammability | Nominal Value | Unit | Test Method |
| Flame Rating | | | UL 94 |
| 0.06 in | • V-0 | | |
| | • 5VB | | |
| 0.12 in | 5VA | | |
| Oxygen Index ³ | 34 | % | ISO 4589-2 |
| Fill Analysis | Nominal Value | Unit | Test Method |
| Melt Viscosity ⁴ (500°F) | 210 | Pa·s | ISO 11443-A |

Processing Information



| Injection | Nominal Value | Unit |
|------------------------------------|------------------|------|
| Drying Temperature - Dry Air Dryer | 176 | °F |
| Drying Time - Dry Air Dryer | 4.0 | hr |
| Suggested Max Moisture | < 0.020 | % |
| Suggested Shot Size | 30 to 70 | % |
| Rear Temperature | 428 to 446 | °F |
| Middle Temperature | 437 to 455 | °F |
| Front Temperature | 446 to 464 | °F |
| Nozzle Temperature | 491 to 509 | °F |
| Processing (Melt) Temp | 464 to 518 | °F |
| Mold Temperature | 140 to 194 | °F |
| Back Pressure | 725 to 2180 | psi |
| Vent Depth | 9.8E-4 to 3.0E-3 | in |

Injection Notes

Hold Pressure (% of Injection Pressure): 50 - 75%
 Peripheral Screw Speed: 0.05 - 0.2 m/s
 Standard Melt Temperature: 260°C

Notes

- ¹ Typical properties: these are not to be construed as specifications.
- ² 150x105x3mm., MT 80°C
- ³ Procedure A
- ⁴ 1000s-1

