

HiFill® PC/ABS 8100 UV BK

 Techmer Polymer Modifiers - *Polycarbonate + ABS*
General Information
General

Material Status	<ul style="list-style-type: none"> Commercial: Active
Availability	<ul style="list-style-type: none"> North America
Additive	<ul style="list-style-type: none"> UV Stabilizer
Features	<ul style="list-style-type: none"> UV Stabilized
Appearance	<ul style="list-style-type: none"> Black
Processing Method	<ul style="list-style-type: none"> Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.09		ASTM D792
Molding Shrinkage - Flow (0.125 in)	5.0E-3 to 7.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	270000	psi	ASTM D638
Tensile Strength (Yield)	6500	psi	ASTM D638
Tensile Strength (Break)	5500	psi	ASTM D638
Tensile Elongation (Break)	8.0	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	3.5	ft·lb/in	ASTM D256

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 3.0	hr
Rear Temperature	500 to 540	°F
Middle Temperature	510 to 550	°F
Front Temperature	520 to 560	°F
Nozzle Temperature	530 to 570	°F
Processing (Melt) Temp	510 to 565	°F
Mold Temperature	150 to 225	°F
Injection Rate	Slow-Moderate	
Back Pressure	25.0 to 75.0	psi
Screw Speed	Slow	

