

HiFill® PC / ABS GF30

 Techmer Polymer Modifiers - *Polycarbonate + ABS*
General Information
General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.34		ASTM D792
Molding Shrinkage - Flow (0.125 in)	4.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.10	%	ASTM D570
Mechanical			
Tensile Strength (Yield)	16900	psi	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	900000	psi	ASTM D790
Flexural Strength	25000	psi	ASTM D790
Impact			
Notched Izod Impact (73°F, 0.125 in)	2.0	ft·lb/in	ASTM D256
Hardness			
Rockwell Hardness (R-Scale)	119		ASTM D785
Thermal			
Deflection Temperature Under Load (264 psi, Unannealed)	240	°F	ASTM D648
CLTE - Flow	2.3E-5	in/in/°F	ASTM D696
Flammability			
Flame Rating	HB		UL 94

