

**InStruc® PCABSGF30**

Americhem - Polycarbonate + ABS

**General Information**
**Product Description**

30% FIBERGLASS REINFORCED POLYCARBONATE/ABS ALLOY

**General**

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Asia Pacific • Europe • Latin America • North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• Filled • Good Dimensional Stability • High Stiffness • High Strength
Uses	• Automotive Applications • Closures • Connectors • Consumer Applications • Electrical/Electronic Applications • Engineering Parts • Household Goods • Housings • Industrial Applications • Industrial Parts • Office Automation Equipment
Forms	• Pellets
Processing Method	• Injection Molding

**Properties <sup>1</sup>**

	Nominal Value	Unit	Test Method
<b>Physical</b>			
Density / Specific Gravity	1.35		ASTM D792
Molding Shrinkage - Flow (0.125 in)	1.0E-3 to 3.0E-3	in/in	
<b>Mechanical</b>			
Tensile Strength (Break)	17000	psi	ASTM D638
Tensile Elongation (Break)	1.0 to 2.0	%	ASTM D638
Flexural Modulus	1.00E+6	psi	ASTM D790
<b>Impact</b>			
Notched Izod Impact	2.0	ft-lb/in	ASTM D256
Unnotched Izod Impact	10 to 12	ft-lb/in	ASTM D4812
<b>Thermal</b>			
Deflection Temperature Under Load (264 psi, Unannealed)	295	°F	ASTM D648
<b>Electrical</b>			
Volume Resistivity	> 1.0E+17	ohms·cm	ASTM D257

**Processing Information**

	Nominal Value	Unit
<b>Injection</b>		
Drying Temperature	200	°F
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.020	%
Processing (Melt) Temp	475 to 510	°F
Mold Temperature	125 to 180	°F
Back Pressure	50.0 to 100	psi
Screw Speed	40 to 70	rpm
Vent Depth	1.0E-3 to 2.0E-3	in

