

Plaslube® APC100 UV

 Techmer Polymer Modifiers - *Polycarbonate + ABS*
General Information
General

Material Status	<ul style="list-style-type: none"> Commercial: Active
Availability	<ul style="list-style-type: none"> North America
Additive	<ul style="list-style-type: none"> UV Stabilizer
Features	<ul style="list-style-type: none"> UV Resistant
Appearance	<ul style="list-style-type: none"> Colors Available
Forms	<ul style="list-style-type: none"> Pellets
Processing Method	<ul style="list-style-type: none"> Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.10		ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
230°C/3.8 kg	5.5	g/10 min	
260°C/5.0 kg	16	g/10 min	
Molding Shrinkage - Flow (0.125 in)	6.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	6600	psi	ASTM D638
Tensile Elongation (Break)	70	%	ASTM D638
Flexural Modulus	290000	psi	ASTM D790
Flexural Strength	10500	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	13	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	115		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	250	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	235	°F	ASTM D648
CLTE - Flow	4.0E-5	in/in/°F	ASTM D696
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

