

TRILOY® 200FT

Samyang Corporation - Polycarbonate + ABS

General Information
Product Description

TRILOY® is the PC based compound resin, designed to meet customer's challenging application requirements.

TRILOY® has good impact resistance, heat resistance, and excellent processability, which makes it suitable for precision parts.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Features	• Flame Retardant
Uses	• Automotive Applications • Automotive Exterior Parts • Automotive Interior Parts
Forms	• Pellets

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.08		ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/2.16 kg)	18	g/10 min	ASTM D1238
Water Absorption (24 hr, 73°F)	0.20	%	ASTM D570
Mechanical			
Tensile Strength (Yield)	7820	psi	ASTM D638
Tensile Elongation (Break)	50	%	ASTM D638
Flexural Modulus	327000	psi	ASTM D790
Flexural Strength (Yield)	12100	psi	ASTM D790
Impact			
Notched Izod Impact (73°F, 0.125 in)	12	ft-lb/in	ASTM D256
Hardness			
Rockwell Hardness (R-Scale)	100		ASTM D785
Thermal			
Deflection Temperature Under Load (264 psi, Unannealed)	212	°F	ASTM D648
CLTE - Flow	4.1E-5	in/in/°F	ASTM D696
Electrical			
Volume Resistivity	5.0E+16	ohms·cm	ASTM D257
Dielectric Strength	640	V/mil	ASTM D149
Dielectric Constant	3.00		ASTM D150
Dissipation Factor	9.0E-3		ASTM D150
Arc Resistance	123	sec	ASTM D495
Flammability			
Flame Rating			UL 94
0.06 in		V-0	
0.08 in		5VB	

