

TRILOY® 210GNH10

Samyang Corporation - Polycarbonate + ABS

General Information

Product Description

TRILOY® is the PC based compound resin, designed to meet customer's challenging application requirements.

TRILOY® has good impact resistance, heat resistance, and excellent processability, which makes it suitable for precision parts.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Uses	• Electrical/Electronic Applications

 Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.31		ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/5.0 kg)	15	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.118 in)	3.0E-3 to 5.0E-3	in/in	ASTM D955
Water Absorption (24 hr, 73°F)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	9960	psi	ASTM D638
Tensile Elongation (Yield)	3.0	%	ASTM D638
Flexural Modulus	540000	psi	ASTM D790
Flexural Strength (Yield)	15600	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	1.3	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	198	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-0		UL 94

