

Electrafil® PC / PET CF20 IM

 Techmer Polymer Modifiers - *Polycarbonate + PET*
General Information
General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Carbon Fiber, 20% Filler by Weight
Additive	• Impact Modifier
Features	• Impact Modified • Semi Conductive
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.31		ASTM D792
Molding Shrinkage - Flow (0.125 in)	6.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.080	%	ASTM D570
Mechanical			
Tensile Strength (Yield)	18000	psi	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	1.35E+6	psi	ASTM D790
Flexural Strength (Yield)	26000	psi	ASTM D790
Impact			
Notched Izod Impact (73°F, 0.125 in)	1.8	ft·lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	6.0	ft·lb/in	ASTM D4812
Hardness			
Rockwell Hardness (R-Scale)	118		ASTM D785
Thermal			
Deflection Temperature Under Load (66 psi, Unannealed)	270	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	252	°F	ASTM D648
CLTE - Flow	1.1E-5	in/in/°F	ASTM D696
Electrical			
Surface Resistivity	1.0E+7	ohms	ASTM D257
Volume Resistivity	1.0E+7	ohms·cm	ASTM D257
Flammability			
Flame Rating (0.06 in)	HB		UL 94

