

InLube® PCPBTF13SI2UV

Americhem - Polycarbonate + PBT

General Information

Product Description

13% PTFE and 2% Silicone Lubricated, UV Stabilized, Polycarbonate/Polybutylene Terephthalate (PBT) Alloy

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• PTFE Lubricant: 13%	• Silicone Lubricant: 2%	• UV Stabilizer
Features	• Chemical Resistant • Good Dimensional Stability • Good Mold Release	• Low Friction • Lubricated • UV Stabilized	• Wear Resistant
Uses	• Automotive Applications • Closures • Connectors • Consumer Applications	• Electrical/Electronic Applications • Engineering Parts • Household Goods • Housings	• Industrial Applications • Industrial Parts • Office Automation Equipment • Outdoor Applications
Forms	• Pellets		
Processing Method	• Injection Molding		

 Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.29		ASTM D792
Molding Shrinkage - Flow (0.125 in)	5.0E-3 to 7.0E-3	in/in	
Water Absorption (Saturation)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	540000	psi	ASTM D638
Tensile Strength	11000	psi	ASTM D638
Tensile Elongation (Break)	3.0 to 5.0	%	ASTM D638
Flexural Modulus	600000	psi	ASTM D790
Flexural Strength	12000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	1.5	ft·lb/in	ASTM D256
Unnotched Izod Impact	10	ft·lb/in	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	295	°F	ASTM D648

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	230	°F
Drying Time	3.0 to 4.0	hr
Processing (Melt) Temp	510 to 530	°F
Mold Temperature	150 to 180	°F
Back Pressure	50.0 to 100	psi
Screw Speed	40 to 70	rpm

