

**HiFill® PC/PBT IM 5720 UV BK**

 Techmer Polymer Modifiers - *Polycarbonate + PBT*
**General Information**
**General**

Material Status	• Commercial: Active
Availability	• North America
Additive	• Impact Modifier      • UV Stabilizer
Features	• Impact Modified      • UV Stabilized
Appearance	• Black
Processing Method	• Injection Molding

**Properties <sup>1</sup>**

<b>Physical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Density / Specific Gravity	1.21		ASTM D792
Molding Shrinkage - Flow (0.125 in)	7.0E-3 to 9.0E-3	in/in	ASTM D955
<b>Mechanical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Modulus	320000	psi	ASTM D638
Tensile Strength (Yield)	7800	psi	ASTM D638
Tensile Strength (Break)	7800	psi	ASTM D638
Tensile Elongation (Break)	80	%	ASTM D638
<b>Impact</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Notched Izod Impact (0.125 in)	11	ft-lb/in	ASTM D256

**Processing Information**

<b>Injection</b>	<b>Nominal Value</b>	<b>Unit</b>
Drying Temperature	180	°F
Drying Time	2.0 to 3.0	hr
Rear Temperature	460 to 500	°F
Middle Temperature	470 to 510	°F
Front Temperature	480 to 520	°F
Nozzle Temperature	490 to 530	°F
Processing (Melt) Temp	465 to 525	°F
Mold Temperature	125 to 175	°F
Injection Rate	Slow	
Back Pressure	25.0 to 75.0	psi
Screw Speed	Slow-Moderate	

