

**HiFill FR® PC/ASA FR1520 UV WT115498**

 Techmer Polymer Modifiers - *Polycarbonate + ASA*
**General Information**
**General**

Material Status	• Commercial: Active
Availability	• North America
Additive	• Flame Retardant      • UV Stabilizer
Features	• Flame Retardant      • UV Stabilized
Appearance	• White
Processing Method	• Injection Molding

**Properties <sup>1</sup>**

<b>Physical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Density / Specific Gravity	1.23		ASTM D792
Molding Shrinkage - Flow (0.125 in)	8.0E-3 to 0.010	in/in	ASTM D955
<b>Mechanical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Modulus	310000	psi	ASTM D638
Tensile Strength (Yield)	8000	psi	ASTM D638
Tensile Strength (Break)	7000	psi	ASTM D638
Tensile Elongation (Break)	> 10	%	ASTM D638
<b>Impact</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Notched Izod Impact (0.125 in)	7.0	ft·lb/in	ASTM D256
<b>Flammability</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Flame Rating			UL 94
0.06 in	V-0		
0.12 in	V-0		

**Processing Information**

<b>Injection</b>	<b>Nominal Value</b>	<b>Unit</b>
Drying Temperature	250	°F
Drying Time	2.0 to 3.0	hr
Rear Temperature	510 to 530	°F
Middle Temperature	520 to 540	°F
Front Temperature	530 to 550	°F
Nozzle Temperature	525 to 545	°F
Processing (Melt) Temp	515 to 550	°F
Mold Temperature	125 to 200	°F
Injection Rate	Slow-Moderate	
Back Pressure	25.0 to 75.0	psi
Screw Speed	Slow	

