

**Plaslube® PC / PBT IM 6200 BK**

 Techmer Polymer Modifiers - *Polycarbonate + PBT*
**General Information**
**General**

Material Status	• Commercial: Active
Availability	• North America
Additive	• Impact Modifier
Features	• High Impact Resistance
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

**Properties <sup>1</sup>**

	Nominal Value	Unit	Test Method
<b>Physical</b>			
Density / Specific Gravity	1.19		ASTM D792
Molding Shrinkage - Flow (0.125 in)	8.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.10	%	ASTM D570
<b>Mechanical</b>			
Tensile Strength (Yield)	6400	psi	ASTM D638
Tensile Elongation (Yield)	90	%	ASTM D638
Flexural Modulus	270000	psi	ASTM D790
Flexural Strength	12200	psi	ASTM D790
<b>Impact</b>			
Notched Izod Impact			ASTM D256
-40°F, 0.125 in	9.0	ft·lb/in	
73°F, 0.125 in	14	ft·lb/in	
<b>Thermal</b>			
Deflection Temperature Under Load (66 psi, Unannealed)	245	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	210	°F	ASTM D648
CLTE - Flow	4.6E-5	in/in/°F	ASTM D696
<b>Electrical</b>			
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
<b>Flammability</b>			
Flame Rating	HB		UL 94

**Processing Information**

	Nominal Value	Unit
<b>Injection</b>		
Drying Temperature	210	°F
Drying Time	4.0	hr
Rear Temperature	460 to 510	°F
Middle Temperature	460 to 510	°F
Front Temperature	460 to 510	°F
Processing (Melt) Temp	460 to 510	°F
Mold Temperature	130 to 200	°F
Back Pressure	25.0 to 60.0	psi
Screw Speed	30 to 60	rpm

