

HiFill® HDPE TM10

Techmer Polymer Modifiers - *High Density Polyethylene*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Talc, 10% Filler by Weight
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.03		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.022	in/in	ASTM D955
Water Absorption (24 hr)	0.020	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	3500	psi	ASTM D638
Tensile Elongation (Break)	20	%	ASTM D638
Flexural Modulus	110000	psi	ASTM D790
Flexural Strength	3700	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	0.50	ft·lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	6.0	ft·lb/in	ASTM D4812
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	30		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	140	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	110	°F	ASTM D648
Melting Temperature	275	°F	
CLTE - Flow	5.2E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	600	V/mil	ASTM D149

