

**InElec® PEEKCF20HF**

Americhem - Polyetheretherketone

## General Information

**Product Description**

20% CARBON FIBER REINFORCED HIGH FLOW POLYETHERETHERKETONE

**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Carbon Fiber, 20% Filler by Weight		
Features	• Electrically Conductive • ESD Protection • Filled	• Good Dimensional Stability • High Flow • High Stiffness	• High Strength • Permanent Antistatic
Uses	• Aerospace Applications • Connectors • Consumer Applications • Electrical/Electronic Applications	• Engineering Parts • Industrial Applications • Industrial Parts • Metal Replacement	• Military/Defense Applications • Oil/Gas Applications • Outdoor Applications • Semiconductor Applications
Forms	• Pellets		
Processing Method	• Injection Molding		

 Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.37		ASTM D792
Molding Shrinkage - Flow	1.0E-3 to 2.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2.60E+6	psi	ASTM D638
Tensile Strength	30000	psi	ASTM D638
Tensile Elongation (Yield)	1.5 to 2.0	%	ASTM D638
Flexural Modulus	2.30E+6	psi	ASTM D790
Flexural Strength	42000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.2	ft·lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	12	ft·lb/in	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	595	°F	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 to 1.0E+6	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-0		Internal Method

## Processing Information

Injection	Nominal Value	Unit
Drying Temperature	300	°F
Drying Time	2.0 to 4.0	hr
Processing (Melt) Temp	660 to 750	°F
Mold Temperature	325 to 425	°F
Back Pressure	50.0 to 100	psi
Screw Speed	40 to 70	rpm

