

**HiFill® PEEK GF20 A**

 Techmer Polymer Modifiers - *Polyetheretherketone*
**General Information**
**General**

Material Status	<ul style="list-style-type: none"> <li>Commercial: Active</li> </ul>
Availability	<ul style="list-style-type: none"> <li>North America</li> </ul>
Filler / Reinforcement	<ul style="list-style-type: none"> <li>Glass Fiber</li> </ul>
Appearance	<ul style="list-style-type: none"> <li>Colors Available</li> </ul>
Processing Method	<ul style="list-style-type: none"> <li>Injection Molding</li> </ul>

**Properties <sup>1</sup>**

	Nominal Value	Unit	Test Method
<b>Physical</b>			
Density / Specific Gravity	1.43		ASTM D792
Molding Shrinkage - Flow (0.125 in)	7.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.12	%	ASTM D570
<b>Mechanical</b>			
Tensile Strength (Break)	23000	psi	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	1.05E+6	psi	ASTM D790
Flexural Strength	30000	psi	ASTM D790
<b>Impact</b>			
Notched Izod Impact (73°F, 0.125 in)	1.7	ft·lb/in	ASTM D256
<b>Hardness</b>			
Rockwell Hardness (R-Scale)	115		ASTM D785
<b>Thermal</b>			
Deflection Temperature Under Load (264 psi, Unannealed)	600	°F	ASTM D648
CLTE - Flow	1.2E-5	in/in/°F	ASTM D696
<b>Electrical</b>			
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
<b>Flammability</b>			
Flame Rating (0.03 in)	V-0		UL 94

**Processing Information**

	Nominal Value	Unit
<b>Injection</b>		
Drying Temperature	300	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	680 to 730	°F
Middle Temperature	680 to 730	°F
Front Temperature	680 to 730	°F
Processing (Melt) Temp	680 to 720	°F
Mold Temperature	350 to 425	°F
Back Pressure	50.0 to 100	psi
Screw Speed	50 to 100	rpm

