

LARPEEK 10 MDT05-01 G/35 NT:0210F1

 LATI INDUSTRIA TERMOPLASTICI SPA - *Polyetheretherketone*
General Information
Product Description

Compound based on Polyetheretherketone (PEEK). Magnetic and X-Rays detectable filler. Glass fibres. Intrinsically flame retardant. Very good chemical resistance. Very good thermal properties. Low smoke density and low toxicity index. PFAS-free product.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Filler	• Glass Fiber	
Features	• Flame Retardant	• Magnetically Detectable	• PFAS Free
	• High Heat Resistance	• Metal Detectable	• X-Ray Detectable
Uses	• High Temperature Applications		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	2.08	g/cm ³	ISO 1183
Molding Shrinkage ²			ISO 294-4
Across Flow : 0.0787 in	0.75 to 1.2	%	
Flow : 0.0787 in	0.40 to 0.60	%	
Water Absorption ³ (Saturation, 73°F)	0.050	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	1.89E+6	psi	ISO 527-1/1
Tensile Stress (Break, 73°F)	19600	psi	ISO 527-2/5
Tensile Strain (Break, 73°F)	1.2	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.9	ft·lb/in ²	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	17	ft·lb/in ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	644	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	626	°F	ISO 75-2/A
Vicat Softening Temperature	644	°F	ISO 306/B120
CLTE - Flow (86 to 212°F)	1.1E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (86 to 212°F)	1.9E-5	in/in/°F	ISO 11359-2
Thermal Conductivity			ASTM E1461
₄	2.1	Btu·in/hr/ft ² /°F	
₅	3.5	Btu·in/hr/ft ² /°F	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	ASTM D257
Comparative Tracking Index ⁶ (Solution A)	125	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.06 in	V-0		
0.12 in	V-0		
Glow Wire Flammability Index (0.08 in)	1760	°F	IEC 60695-2-12
Glow Wire Ignition Temperature (0.08 in)	1520	°F	IEC 60695-2-13

