

LUVOCOM® 1105-50336/BK

LEHOSS Group - Polyetheretherketone

General Information

Product Description

with CNT; black

Main Features

- Highly chemically- and hydrolysis- resistant parts, non flammable.
- Dynamically-stressed parts.
- Strong, stiff parts.
- Electrically conductive, suitable for continuous discharging of statically-generated electricity.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Carbon Nano		
Features	• Chemical Resistant	• High Stiffness	• Hydrolysis Resistant
	• Electrically Conductive	• High Strength	• Ignition Resistant
Appearance	• Black		

 Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.31	g/cm ³	ISO 1183
Water Absorption (24 hr, 73°F)	< 0.10	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	725000	psi	ISO 527-1/1
Tensile Stress	15200	psi	ISO 527-2
Tensile Strain (Yield)	4.9	%	ISO 527-2/50
Flexural Modulus ²	580000	psi	ISO 178
Flexural Stress ³	24700	psi	ISO 178
Flexural Strain - (Yield) ⁴	6.8	%	ISO 178
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature ⁵	482	°F	IEC 60216
Service Temperature - during lifetime max. 200 hr	536	°F	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+6 to 1.0E+9	ohms	IEC 62631-3-2
Insulation Resistance ⁶	1.0E+6 to 1.0E+9	ohms	IEC 62631-3-3

Processing Information

Injection	Nominal Value	Unit
Drying Temperature		
Desiccant Dryer, A	302	°F
Desiccant Dryer, B	248	°F
Drying Time		
Desiccant Dryer, A	3.0 to 6.0	hr
Desiccant Dryer, B	6.0 to 8.0	hr
Rear Temperature	680 to 698	°F
Middle Temperature	716 to 734	°F
Front Temperature	734 to 752	°F
Nozzle Temperature	680 to 716	°F
Processing (Melt) Temp	734	°F
Mold Temperature	338 to 392	°F



Injection Notes

During processing, the moisture level should not exceed 0.01%, otherwise molecular degradation may occur. As the material absorbs water very quickly, the predried material should be fed to the processing immediately. The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application. Please contact us for further information.

Notes

¹ Typical properties: these are not to be construed as specifications.

² 0.079 in/min

³ 0.39 in/min

⁴ 10 mm/min

⁵ 20,000 hr

⁶ strip electrode R25

