

**LUVOCOM® 1105-8199**

LEHOSS Group - Polyetheretherketone

**General Information**
**Product Description**

with CNT; black

**Main Features**

- Chemically- and hydrolytically- resistant parts, non flammable.
- Electrically conductive, suitable for continuous discharging of statically-generated electricity.
- Highly dimensionally stable at elevated temperatures.

**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Carbon Nano		
Features	• Chemical Resistant	• High Dimensional Stability	• Ignition Resistant
	• Electrically Conductive	• Hydrolytically Stable	
Appearance	• Black		

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density	1.33	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage			DIN 16742
Across Flow	1.4 to 1.6	%	
Flow	1.4 to 1.6	%	
Water Absorption (24 hr, 73°F)	< 0.10	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	725000	psi	ISO 527-1/1
Tensile Stress	13800	psi	ISO 527-2
Tensile Strain (Yield)	2.5	%	ISO 527-2/50
Flexural Modulus <sup>2</sup>	653000	psi	ISO 178
Flexural Stress <sup>3</sup>	26100	psi	ISO 178
Flexural Strain - (Yield) <sup>4</sup>	5.5	%	ISO 178
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature <sup>5</sup>	482	°F	IEC 60216
Service Temperature - during lifetime max. 200 hr	500	°F	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	< 1.0E+6	ohms	IEC 62631-3-2
Insulation Resistance <sup>6</sup>	< 1.0E+5	ohms	IEC 62631-3-3
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-0		Internal Method

**Processing Information**

Injection	Nominal Value	Unit
Drying Temperature		
Desiccant Dryer, A	302	°F
Desiccant Dryer, B	248	°F
Drying Time		
Desiccant Dryer, A	3.0 to 6.0	hr
Desiccant Dryer, B	6.0 to 8.0	hr
Rear Temperature	680 to 698	°F



Middle Temperature	716 to 734 °F
Front Temperature	734 to 752 °F
Nozzle Temperature	680 to 716 °F
Processing (Melt) Temp	734 °F
Mold Temperature	338 to 392 °F

#### Injection Notes

During processing, the moisture level should not exceed 0.01%, otherwise molecular degradation may occur. As the material absorbs water very quickly, the predried material should be fed to the processing immediately. The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application. Please contact us for further information.

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 0.079 in/min

<sup>3</sup> 0.39 in/min

<sup>4</sup> 10 mm/min

<sup>5</sup> 20,000 hr

<sup>6</sup> strip electrode R25

