

**LUVOCOM® 1105-7460/BL5019**

LEHOSS Group - Polyetheretherketone

**General Information**
**Product Description**

with glass fibers; capri blue

**Main Features**

- Strong, stiff, impact-resistant parts.
- Chemically- and hydrolytically- resistant parts, non flammable.
- High dimensionally stable precision parts, high continuous use temperature.

**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Glass Fiber		
Features	• Chemical Resistant	• High Impact Resistance	• Hydrolytically Stable
	• High Dimensional Stability	• High Stiffness	• Ignition Resistant
	• High Heat Resistance	• High Strength	
Appearance	• Blue		

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density	1.58	g/cm <sup>3</sup>	ISO 1183
Water Absorption (24 hr, 73°F)	< 0.10	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	957000	psi	ISO 527-1/1
Tensile Stress	13100	psi	ISO 527-2
Tensile Strain (Yield)	2.5	%	ISO 527-2/50
Flexural Modulus <sup>2</sup>	798000	psi	ISO 178
Flexural Stress <sup>3</sup>	21000	psi	ISO 178
Flexural Strain - (Yield) <sup>4</sup>	3.1	%	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	23	ft·lb/in <sup>2</sup>	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature <sup>5</sup>	482	°F	IEC 60216
Vicat Softening Temperature	617	°F	ISO 306/A
Service Temperature - during lifetime max. 200 hr	500	°F	
Electrical	Nominal Value	Unit	Test Method
Insulation Resistance <sup>6</sup>	> 1.0E+12	ohms	IEC 62631-3-3

**Processing Information**

Injection	Nominal Value	Unit
Drying Temperature		
Desiccant Dryer, A	302	°F
Desiccant Dryer, B	248	°F
Drying Time		
Desiccant Dryer, A	3.0 to 6.0	hr
Desiccant Dryer, B	6.0 to 8.0	hr
Rear Temperature	680 to 698	°F
Middle Temperature	716 to 734	°F
Front Temperature	734 to 752	°F
Nozzle Temperature	680 to 716	°F



Processing (Melt) Temp	734 °F
Mold Temperature	338 to 392 °F

### Injection Notes

During processing, the moisture level should not exceed 0.01%, otherwise molecular degradation may occur. As the material absorbs water very quickly, the predried material should be fed to the processing immediately. The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application. Please contact us for further information.

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 0.079 in/min

<sup>3</sup> 0.39 in/min

<sup>4</sup> 10 mm/min

<sup>5</sup> 20,000 hr

<sup>6</sup> strip electrode R25

