

Plaslube® PEEK CF10 TL15 HF

Techmer Polymer Modifiers - *Polyetheretherketone*

General Information

General		
Material Status	• Commercial: Active	
Availability	• North America	
Filler / Reinforcement	• Carbon Fiber	
Additive	• PTFE Lubricant	
Features	• High Flow	• Lubricated
Appearance	• Black	
Processing Method	• Injection Molding	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.43		ASTM D792
Molding Shrinkage - Flow (0.125 in)	2.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.15	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	26000	psi	ASTM D638
Tensile Elongation (Break)	1.5	%	ASTM D638
Flexural Modulus	1.80E+6	psi	ASTM D790
Flexural Strength	38000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	1.2	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	570	°F	ASTM D648
CLTE - Flow	6.0E-6	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+5	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-0		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	300	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	680 to 730	°F
Middle Temperature	680 to 730	°F
Front Temperature	680 to 730	°F
Processing (Melt) Temp	680 to 720	°F
Mold Temperature	350 to 425	°F
Back Pressure	50.0 to 100	psi
Screw Speed	50 to 100	rpm

