

Plaslube® PEEK 13004

 Techmer Polymer Modifiers - *Polyetheretherketone*
General Information
General

Material Status	• Commercial: Active
Availability	• North America
Additive	• PTFE Lubricant
Features	• High Viscosity • Lubricated
Processing Method	• Injection Molding

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.30		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.016	in/in	ASTM D955
Water Absorption (24 hr)	0.12	%	ASTM D570
Mechanical			
Tensile Strength (Yield)	12000	psi	ASTM D638
Tensile Elongation (Yield)	5.0	%	ASTM D638
Flexural Modulus	500000	psi	ASTM D790
Flexural Strength	18000	psi	ASTM D790
Impact			
Notched Izod Impact (73°F, 0.125 in)	1.0	ft·lb/in	ASTM D256
Hardness			
Rockwell Hardness (R-Scale)	105		ASTM D785
Thermal			
Deflection Temperature Under Load (264 psi, Unannealed)	315	°F	ASTM D648
CLTE - Flow	2.6E-5	in/in/°F	ASTM D696
Electrical			
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Dielectric Strength	300	V/mil	ASTM D149
Flammability			
Flame Rating (0.031 in)	V-0		UL 94

Processing Information

	Nominal Value	Unit
Injection		
Drying Temperature	300	°F

