

**LUVOCOM® 1106-7940/GY/EM**

 LEHOSS Group - *Polyetherimide*
**General Information**
**Product Description**

unreinforced, laser markable; light grey

**Main Features**

- High continuous-use and heat-distortion temperatures. Non flammable.
- Dynamically-stressed parts moving at high velocity.
- High dimensionally stable precision parts.

**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Features	• High Dimensional Stability	• Ignition Resistant	
	• High Heat Resistance	• Laser Markable	
Appearance	• Light Grey		

**Properties <sup>1</sup>**

<b>Physical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Density	1.45	g/cm <sup>3</sup>	ISO 1183
Water Absorption (24 hr, 73°F)	< 0.30	%	ISO 62
<b>Mechanical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Modulus	551000	psi	ISO 527-1/1
Tensile Stress	16700	psi	ISO 527-2
Tensile Strain (Yield)	6.5	%	ISO 527-2/50
Flexural Modulus <sup>2</sup>	479000	psi	ISO 178
Flexural Stress <sup>3</sup>	23900	psi	ISO 178
Flexural Strain - (Yield) <sup>4</sup>	8.0	%	ISO 178
<b>Impact</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Charpy Notched Impact Strength	2.4	ft-lb/in <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength	40	ft-lb/in <sup>2</sup>	ISO 179/1eU
<b>Thermal</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Deflection Temperature Under Load (264 psi, Unannealed)	392	°F	ISO 75-2/A
Continuous Use Temperature <sup>5</sup>	338	°F	IEC 60216
<b>Electrical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Surface Resistivity	> 1.0E+12	ohms	IEC 62631-3-2
Insulation Resistance <sup>6</sup>	> 1.0E+12	ohms	IEC 62631-3-3
<b>Flammability</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Flame Rating (0.06 in)	V-0		Internal Method

**Processing Information**

<b>Injection</b>	<b>Nominal Value</b>	<b>Unit</b>
Drying Temperature		
Desiccant Dryer, A	248	°F
Desiccant Dryer, B	302	°F
Drying Time		
Desiccant Dryer, A	> 8.0	hr
Desiccant Dryer, B	> 4.0	hr
Rear Temperature	680 to 716	°F
Middle Temperature	680 to 716	°F



Front Temperature	698 to 734 °F
Nozzle Temperature	716 to 752 °F
Processing (Melt) Temp	716 °F
Mold Temperature	320 to 374 °F

#### Injection Notes

During processing, the moisture level should not exceed 0.01%, otherwise molecular degradation may occur. As the material absorbs water very quickly, the predried material should be fed to the processing immediately. The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application. Please contact us for further information.

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 0.079 in/min

<sup>3</sup> 0.39 in/min

<sup>4</sup> 10 mm/min

<sup>5</sup> 20,000 hr

<sup>6</sup> strip electrode R25

