

HiFill® PET 0268 B1

 Techmer Polymer Modifiers - *Polyethylene Terephthalate*
General Information
General

Material Status	<ul style="list-style-type: none"> Commercial: Active
Availability	<ul style="list-style-type: none"> North America
Filler / Reinforcement	<ul style="list-style-type: none"> Barium Sulfate
Appearance	<ul style="list-style-type: none"> Colors Available
Forms	<ul style="list-style-type: none"> Pellets
Processing Method	<ul style="list-style-type: none"> Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	2.68		ASTM D792
Molding Shrinkage - Flow (0.125 in)	4.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	11500	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	850000	psi	ASTM D790
Flexural Strength	17000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	0.90	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+13 to 1.0E+14	ohms·cm	ASTM D257

Notes
¹ Typical properties: these are not to be construed as specifications.
