

TRIPET® LV2550GN30

Samyang Corporation - Polyethylene Terephthalate

General Information

Product Description

TRIPET® has excellent mechanical properties and dimensional stability, and good electrical property, widely used in the field of automobile, electric & electronics.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Uses	• General Purpose
Forms	• Pellets

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.61		ASTM D792
Melt Mass-Flow Rate (MFR) (265°C/5.0 kg)	60	g/10 min	ASTM D1238
Molding Shrinkage - Flow	2.0E-3 to 4.0E-3	in/in	ASTM D955
Water Absorption (24 hr, 73°F)	< 0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	19900	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	1.28E+6	psi	ASTM D790
Flexural Strength (Yield)	25600	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	1.1	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	117		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	428	°F	ASTM D648
CLTE - Flow	1.7E-5	in/in/°F	ASTM D696
RTI Elec (0.12 in)	302	°F	UL 746B
RTI Imp (0.12 in)	302	°F	UL 746B
RTI Str (0.12 in)	302	°F	UL 746B
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	510	V/mil	ASTM D149
Dielectric Constant	3.80		ASTM D150
Dissipation Factor	0.017		ASTM D150
Arc Resistance	80.0	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.030 in	V-0		
0.06 in	5VA		

